



Europäisches Patentamt
European Patent Office
Office européen des brevets



(11) **EP 0 776 909 B1**

(12)

EUROPEAN PATENT SPECIFICATION

(45) Date of publication and mention
of the grant of the patent:
19.11.2003 Bulletin 2003/47

(51) Int Cl.7: **C08F 4/642, C08F 10/02,
C08F 232/00, B29C 45/00**

(21) Application number: **95928617.0**

(86) International application number:
PCT/JP95/01639

(22) Date of filing: **18.08.1995**

(87) International publication number:
WO 96/006117 (29.02.1996 Gazette 1996/10)

(54) **HIGH DENSITY ETHYLENE POLYMER AND METHOD FOR PRODUCING THE SAME**
ETHYLENPOLYMER HOHER DICHTHE UND VERFAHREN ZU DESSEN HERSTELLUNG
POLYMERE ETHYLENIQUE A HAUTE DENSITE ET SON PROCEDE DE PRODUCTION

(84) Designated Contracting States:
BE DE ES

(30) Priority: **18.08.1994 JP 21521894**

(43) Date of publication of application:
04.06.1997 Bulletin 1997/23

(73) Proprietor: **Asahi Kasei Kabushiki Kaisha**
Osaka-shi, Osaka 530-8205 (JP)

(72) Inventors:
• **MATSUSHITA, Fumio**
Okayama-ken 710 (JP)

• **YAMAGUCHI, Fumihiko 108, Asahi Kasei Kogyo**
Shinden Kurashiki-shi Okayama-ken 710 (JP)
• **IDEHARA, Tsutomu 206, Asahi Kasei Kogyo**
Kurashiki
Kurashiki-shi Okayama-ken 710 (JP)

(74) Representative: **Strehl Schübel-Hopf & Partner**
Maximilianstrasse 54
80538 München (DE)

(56) References cited:
EP-A- 0 516 458 **JP-A- 2 167 311**
JP-A- 4 224 808 **JP-A- 4 225 004**
JP-A- 5 331 232 **JP-A- 61 276 805**

Note: Within nine months from the publication of the mention of the grant of the European patent, any person may give notice to the European Patent Office of opposition to the European patent granted. Notice of opposition shall be filed in a written reasoned statement. It shall not be deemed to have been filed until the opposition fee has been paid. (Art. 99(1) European Patent Convention).

EP 0 776 909 B1

Description

BACKGROUND OF THE INVENTION5 Field of The Invention

[0001] The present invention relates to a high density ethylene polymer and a method for producing the same. More particularly, the present invention is concerned with a high density ethylene polymer which is advantageous in that it has not only excellent mechanical properties, such as high impact resistance and high stiffness, but also excellent moldability, such as high melt flowability, and a method for producing the same.

Prior Art

[0002] High density ethylene polymers have been put into a wide variety of practical uses in the form of molded articles produced by various molding methods. For example, as a representative method for obtaining a molded film, there can be mentioned an inflation method in which a high density ethylene polymer is melted and the resultant molten polymer is extruded through a die while blowing air into the molten polymer being extruded, to thereby inflate the molten polymer extrudate. Further, as examples of methods for producing molded articles having desired shapes, there can be mentioned a blow molding method in which a high density ethylene polymer in the molten state is introduced into the cavity of a mold to form a molten polymer mass in the cavity. Air is blown into the molten polymer mass in the mold cavity, thereby causing the molten polymer mass to be expanded and pressed onto the inner wall of the cavity. Also an injection molding method is known in which a high density ethylene polymer in the molten state is injected under pressure into the cavity of a mold to fill the cavity.

[0003] To all of these various molding methods for high density ethylene polymers, it is common that a melt-molding operation be performed in which a high density ethylene polymer is melted by heating and the resultant molten polymer is molded. Therefore, the behavior of the high density ethylene polymer at heat-melting, i.e., melt properties, are extremely important in molding the high density ethylene polymer.

[0004] Especially in the injection molding method, melt properties, especially melt flowability, of a high density ethylene polymer are crucially important for achieving a satisfactory molding.

[0005] In the present invention, the term "melt flowability" means a property corresponding to the extrusion load at extrusion of a molten resin through an extruder. As examples of indices which can be used as a yardstick for melt flowability, there can be mentioned M_I , H_{MI} and M_{IR} .

[0006] In the present invention, M_I means an MFR (melt flow rate) as measured at 190 °C under a load of 2.16 kg. H_{MI} means an MFR as measured at 190 °C under a load of 21.6 kg. M_{IR} means the ratio of H_{MI} to M_I , that is, H_{MI}/M_I .

[0007] In general, with respect to each of M_I , H_{MI} and M_{IR} , the larger the value, the higher the melt flowability.

[0008] However, in practice, the desired properties of a polymer as a molding material vary depending on the molding method employed. Therefore, which index can be suitably used as a yardstick for melt flowability varies depending on the molding method employed. For example, in the injection molding method, for surely obtaining a molded product having high impact resistance, there is a tendency to use a high density ethylene polymer having a narrow molecular weight distribution. In general, a high density ethylene polymer having a narrow molecular weight distribution has a small M_{IR} , so that, as an index for melt flowability, M_I and H_{MI} are mainly used.

[0009] Conventionally, a high density ethylene polymer for use in the injection molding method has generally been produced by a polymerization using a Ziegler-Natta catalyst, which contains titanium, or using a chromium-containing catalyst. However, in general, a high density ethylene polymer produced by using such a conventional catalyst tends to have a broad molecular weight distribution, and it has been impossible to render a molecular weight distribution narrower than a certain breadth. In order to solve this problem, it has been attempted to improve the moldability of a high density ethylene polymer to be used for injection molding by lowering the molecular weight of the polymer so that the values M_I and H_{MI} can be increased. However, this attempt has led to a disadvantage in that the produced high density ethylene polymer virtually contains extremely low molecular weight components, so that the mechanical properties, such impact resistance, of the polymer are markedly lowered. That is, when good mechanical properties are desired, M_I and the like cannot be largely increased. This means that, for example, injection molding cannot be performed at a high rate.

[0010] On the other hand, it has recently been found that when a catalyst system comprising a solvent-soluble transition metal compound containing at least one halogen, such as bis(cyclopentadienyl)zirconium dichloride, and an aluminoxane is used for homopolymerization of ethylene or copolymerization of ethylene with an α -olefin, the catalyst system exhibits high polymerization activity. With respect to the details of this technique, reference can be made to, for example, Examined Japanese Patent Application Publication No. 4-12283 (corresponding to DE 3127133.2). Further, an improved technique over the technique disclosed in the above-mentioned Examined Japanese Patent Appli-

cation Publication No. 4-12283 is disclosed in, for example, Unexamined Japanese Patent Application Laid-Open Specification No. 60-35007. The catalyst system proposed in these prior art documents is attracting attention as the so-called metallocene catalyst system. By using such a metallocene catalyst system, an ethylene polymer having a narrow molecular weight distribution can be produced, wherein, when the ethylene polymer produced is an ethylene copolymer, the copolymer has not only a narrow molecular weight distribution, but also a narrow copolymerization distribution (i.e., narrow distribution with respect to the proportions of different component monomer units constituting the copolymer). By virtue of having a narrow molecular weight distribution, an ethylene polymer produced by using such a metallocene catalyst system has advantages in that it has high mechanical properties, such as high impact resistance, that it is substantially free of low molecular weight components and high molecular weight components (both of which pose problems, such as high tack and gelation), and that it has excellent properties, such as high resistance to solvent extraction and high transparency. Therefore, energetic researches have conventionally been made on the use of a metallocene catalyst system mainly for producing, for example, a linear low density ethylene polymer (LLDPE), a very low density ethylene polymer (VLDPE) and an ultralow density ethylene polymer (ULDPE). As mentioned above, on one hand, an ethylene polymer produced by using a metallocene catalyst system has such great advantages by virtue of the narrow molecular weight distribution thereof; however, on the other hand, such an ethylene polymer has a problem in that it has an extremely poor moldability due to its narrow molecular weight distribution. Because of this problem, conventionally, with respect to the development of the application of a metallocene catalyst system in production of high density ethylene polymers, which are required to have a good balance between mechanical properties and moldability, a remarkable progress has not yet been achieved.

[0011] In order to solve the above-mentioned problem, it has been proposed to broaden a molecular weight distribution by using, for example, a method in which use is made of a plurality of reactors or a method in which use is made of a plurality of types of metallocene catalysts in combination. Specifically, Unexamined Japanese Patent Application Laid-Open Specification No. 60-35008 proposes a method for rendering a broad molecular weight distribution wherein use is made of a mixture of at least two types of transition metal compounds as a catalyst. Further, a method for rendering a broad molecular weight distribution by using a customary multi-step polymerization process is known. For example, Unexamined Japanese Patent Application Laid-Open Specification No. 3-234717 discloses a method for improving the melt properties of a polymer, wherein a multi-step polymerization process is performed by using an olefin polymerization catalyst comprising a transition metal compound and an organoaluminumoxy compound. Further, for example, in Unexamined Japanese Patent Application Laid-Open Specification Nos. 61-57638, 6-49287, 6-136195 and 6-206939, it is attempted to improve the moldability of a polymer by taking a measure to broaden the molecular weight distribution. When these conventional methods for rendering a broad molecular weight distribution are used, the moldability is improved; however, a lowering of other properties inevitably occurs, so that it becomes impossible to obtain a high density ethylene polymer product having excellent properties, such as high mechanical properties, which are achieved by a narrow molecular weight distribution.

[0012] For example, EP-A-0 516 458 discloses a method for the production of an ethylene polymer or copolymer in the presence of a catalyst comprising : (A) a transition metal compound, such as bisindenylzirconium dichloride or bis(1,3-dimethylcyclopentadienyl) zirconium dichloride, (B) (b-1) an inorganic solid component having hydroxy groups on the surface thereof and, carried thereon, (b-2) an organoaluminumoxy compound, and (C) an organoaluminum compound, such as triisobutylaluminum. However, the method is carried out in a manner wherein component (A) and (b-2), which are both carried on (b-1), and optionally (C) are introduced into a polymerization reaction system. This results in a (co) polymer which is unsatisfactorily compatible with mechanical properties (in particular, impact resistance and stiffness) and moldability.

[0013] In Unexamined Japanese Patent Application Laid-Open Specification Nos. 7-90021 and 7-97408, with respect to the production of a film by inflation molding, it is attempted to improve moldability, such as the stability of a bubble (i.e., a molten polymer tube inflated for forming a film therefrom), by a method in which melt tension is increased by maintaining a relatively high intrinsic viscosity. However, such a method has a problem in that a lowering of melt flowability inevitably occurs, so that it becomes difficult to perform molding at a high rate.

[0014] In order to solve these problems, in the production of an ethylene copolymer by using a metallocene catalyst, it has recently been attempted to produce an ethylene copolymer which is advantageous in that it not only has both a narrow copolymerization distribution and a narrow molecular weight distribution, but also has excellent melt properties. For example, International Patent Application Publication No. WO93/08221 proposes a method for producing an ethylene copolymer having improved melt flowability while maintaining a narrow molecular weight distribution thereof. In this proposed method, copolymerization is performed by using a specific metallocene catalyst to thereby cause the ethylene copolymer to have a long branched chain. However, such an ethylene copolymer has a problem in that, although the melt flowability is improved to some extent, the mechanical properties, such as impact resistance, are considerably lowered, as compared with those of an ethylene copolymer produced by using an ordinary metallocene catalyst.

[0015] As described hereinabove, the prior art techniques have problems in that it is impossible to obtain an excellent

high density ethylene polymer having both excellent mechanical properties and high melt flowability.

[0016] Therefore, if an excellent high density ethylene polymer having both excellent mechanical properties and high melt flowability is obtained, the above-mentioned problems accompanying the ethylene polymer produced by using a titanium-containing Ziegler-Natta catalyst or a chromium-containing catalyst, and also the above-mentioned problems accompanying the ethylene polymer produced by using a conventional metallocene catalyst can be completely solved and the application fields of ethylene polymers can be greatly expanded. That is, such an excellent high density ethylene polymer is of extremely great commercial significance.

SUMMARY OF THE INVENTION

[0017] The present inventors have made extensive and intensive studies with a view toward developing a novel high density ethylene polymer having both excellent mechanical properties and high melt flowability. As a result, it has surprisingly been found that, by using a specific metallocene catalyst selected from among the metallocene catalysts previously developed by the present inventors as olefin polymerization catalysts especially useful for producing a low density ethylene polymer (see International Patent Application Publication No. WO95/15985), a high density ethylene polymer having both excellent mechanical properties and high melt flowability can be obtained, so that the obtained high density ethylene polymer can exhibit both extremely high mechanical strength and extremely excellent moldability. The present invention has been completed, based on this novel finding.

[0018] Accordingly, it is an object of the present invention to provide a high density ethylene polymer which is advantageous in that it has not only excellent mechanical properties, such as high impact resistance and high stiffness, but also excellent moldability, such as high melt flowability.

[0019] It is another object of the present invention to provide a method for producing the above-mentioned excellent high density ethylene polymer effectively and efficiently.

[0020] The foregoing and other objects, features and advantages of the present invention will be apparent from the following detailed description and appended claims taken in connection with the accompanying drawings.

BRIEF DESCRIPTION OF THE DRAWINGS

[0021] In the accompanying drawings:

Fig. 1 shows the relationship between the M_I and the Izod impact strength with respect to each of the high density ethylene polymers of the present invention, in comparison with the relationship between those of each of the comparative ethylene polymers;

Fig. 2 shows the relationship between the M_I and the density with respect to each of the high density ethylene polymers of the present invention, in comparison with the relationship between those of each of the comparative ethylene polymers;

Fig. 3 shows the relationship between the M_I and the M_{IR} with respect to each of high density ethylene polymers of the present invention, in comparison with the relationship between those of each of comparative ethylene polymers; and

Fig. 4 shows the molecular weight distribution curve (which is indicated by a bold line) of the high density ethylene polymer obtained in Example 1, together with a plurality of Gaussian distribution curves (which are indicated by thin lines) obtained by the resolution of the molecular weight distribution curve.

DESCRIPTION OF THE INVENTION

[0022] In one aspect of the present invention, there is provided a high density ethylene polymer comprising a homopolymer of ethylene, or a copolymer of ethylene with at least one comonomer selected from the group consisting of an α -olefin, a cyclic olefin, and linear, branched and cyclic dienes, and having the following properties (a) to (h):

(a) a density d (g/cm^3) of from 0.951 to 0.980;

(b) an M_I ($\text{g}/10$ minutes) of more than 5 and not more than 100, wherein M_I is defined as the melt flow rate as measured at 190 °C under a load of 2.16 kg;

(c) the ethylene polymer satisfying the following relationship:

$$\log a_{kl} \geq -0.844 \log M_I + 1.462$$

wherein M_I is as defined above, and a_{kl} represents the Izod impact strength ($\text{kgf}\cdot\text{cm}/\text{cm}^2$);

(d) the ethylene polymer satisfying the following relationship:

$$\log M_{IR} \cong -0.094 \log M_I + 1.520$$

wherein M_I is as defined above, and M_{IR} represents the H_{MI}/M_I ratio in which H_{MI} (g/10 minutes) is defined as the melt flow rate as measured at 190 °C under a load of 21.6 kg and M_I is as defined above; wherein (e) the density d (g/cm³) and the M_I (g/10 minutes) satisfy the following relationship:

$$d \cong -0.00873 \log M_I + 0.972,$$

and

(f) said M_{IR} is not less than 25 and not more than 40;

(g) an Mw of 30,000 or more, wherein Mw is defined as a weight average molecular weight measured by gel permeation chromatography; and

(h) an Mw/Mn ratio in the range of from 5.0 to 10.0, wherein Mw and Mn, respectively, represent the weight average molecular weight and the number average molecular weight, each measured by gel permeation chromatography.

[0023] The above-mentioned high density ethylene polymer is a novel high density ethylene polymer which has an excellent balance between various properties, such as impact resistance, stiffness and melt flowability.

[0024] For easy understanding of the present invention, the essential features and various preferred embodiments of the present invention are enumerated below.

1. A high density ethylene polymer comprising a homopolymer of ethylene, or a copolymer of ethylene with at least one comonomer selected from the group consisting of an α -olefin, a cyclic olefin, and linear, branched and cyclic dienes, and having the following properties (a) to (h):

(a) a density d (g/cm³) of from 0.951 to 0.980;

(b) an M_I (g/10 minutes) of more than 5 and not more than 100, wherein M_I is defined as the melt flow rate as measured at 190 °C under a load of 2.16 kg;

(c) the ethylene polymer satisfying the following relationship:

$$\log a_{KI} \cong -0.844 \log M_I + 1.462$$

wherein M_I is as defined above, and a_{KI} represents the Izod impact strength (kgf-cm/cm²);

(d) the ethylene polymer satisfying the following relationship:

$$\log M_{IR} \cong -0.094 \log M_I + 1.520$$

wherein M_I is as defined above, and M_{IR} represents the H_{MI}/M_I ratio in which H_{MI} (g/10 minutes) is defined as the melt flow rate as measured at 190 °C under a load of 21.6 kg and M_I is as defined above; wherein

(e) the density d (g/cm³) and the M_I (g/10 minutes) satisfy the following relationship:

$$d \cong -0.00873 \log M_I + 0.972,$$

and

(f) the above-mentioned M_{IR} is not less than 25 and not more than 40;

(g) an Mw of 30,000 or more, wherein Mw is defined as a weight average molecular weight measured by gel permeation chromatography; and

(h) an Mw/Mn ratio in the range of from 5.0 to 10.0, wherein Mw and Mn, respectively, represent the weight average molecular weight and the number average molecular weight, each measured by gel permeation chromatography.

2. The high density ethylene polymer according to item 1 above, which is an injection molding material.

3. The high density ethylene polymer according to items 1 or 2 above, wherein the density d is 0.955 or more.

4. The high density ethylene polymer according to any one of items 1 to 3 above, which is a copolymer of ethylene with at least one comonomer selected from the group consisting of a C₃-C₂₀ cyclic olefin, C₄-C₂₀ linear and cyclic dienes, C₅-C₂₀ branched dienes and an α-olefin represented by the formula H₂C = CHR¹⁵ wherein R¹⁵ is methyl, ethyl, a C₃-C₁₈ linear, branched or cyclic alkyl group or a C₆-C₂₀ aryl group, the comonomer being present in an amount of not more than 1 mole %, based on the total number of moles of all monomer units constituting the ethylene polymer.

5. The ethylene polymer according to item 4 above, wherein the comonomer is selected from the group consisting of propylene, 1-butene, 1-pentene, 1-hexene, 4-methyl-1-pentene, 1-octene, 1-decene, 1-dodecene, 1-tetradecene, 1-hexadecene, 1-octadecene, 1-eicosene, vinylcyclohexane, cyclopentene, cycloheptene, norbornene, 5-methyl-2-norbornene, tetracyclododecene, 2-methyl-1,4, 5,8-dimethano-1,2,3,4,4a,5,8,8a-octahydronaphthalene, 1,3-butadiene, 1,4-pentadiene, 1,5-hexadiene, 1,4-hexadiene, and cyclohexadiene.

6. A method for producing a high density ethylene polymer of item 1 above, which comprises homopolymerizing ethylene or copolymerizing ethylene with at least one comonomer selected from the group consisting of an α-olefin, a cyclic olefin, and linear, branched and cyclic dienes, in the presence of a catalyst comprising the following components (A), (B) and (C):

(A) a transition metal compound represented by the formula (1)



wherein:

M represents a transition metal selected from the group consisting of zirconium, titanium and hafnium; each of R¹ and R² independently represents:

an indenyl group which is unsubstituted or substituted with at least one substituent selected from the group consisting of a C₁-C₂₀ alkyl group, a C₆-C₂₀ aryl group, an aralkyl group having a C₁-C₂₀ alkyl group substituted with at least one C₆-C₂₀ aryl group, and an alkylaryl group having a C₆-C₂₀ aryl group substituted with at least one C₁-C₂₀ alkyl group, wherein each alkyl group is independently of a linear, a branched or a cyclic configuration and wherein at least one carbon atom of the at least one substituent is optionally replaced by a silicon atom, the substituted indenyl group optionally having a substitution in which at least two positions thereof together are substituted with one substituent group, having a valence of two or more, derived from a substituent selected from the at least one substituent, optionally having at least one substituent thereof bonded thereto through an oxygen, a nitrogen, a sulfur or a phosphorus atom;

each of R³ and R⁴ independently represents a hydrogen atom, a halogen atom, a C₁-C₂₀ alkyl group, a C₆-C₂₀ aryl group, an aralkyl group having a C₁-C₂₀ alkyl group substituted with at least one C₆-C₂₀ aryl group, an alkylaryl group having a C₆-C₂₀ aryl group substituted with a C₁-C₂₀ alkyl group, or a -SO₃R⁵ group wherein R⁵ is a C₁-C₈ hydrocarbon group which is unsubstituted or substituted with at least one halogen atom, wherein each alkyl group is independently of a linear, a branched or a cyclic configuration and wherein at least one carbon atom of at least one of the alkyl, aryl, aralkyl and alkylaryl groups is optionally replaced by a silicon atom; and each of R¹, R², R³ and R⁴ is bonded to the transition metal M;

(B) an inorganic solid component comprising a particulate inorganic solid (b-1) having hydroxyl groups on a surface thereof and, carried thereon, an organoaluminumoxy compound (b-2) having repeating alkyloxyaluminum units each represented by the formula (5)



wherein R^6 represents a $\text{C}_1\text{-C}_{12}$ linear, branched or cyclic alkyl group; and
(C) an organoaluminum compound,

wherein components (B) and (C) are intimately mixed and contacted with each other to form an intimate mixture of components (B) and (C), and the intimate mixture and component (A) are separately introduced into a system for homopolymerizing or copolymerizing ethylene, followed by polymerization.

7. The method according to item 6 above, wherein the component (C) is a compound represented by the following formula (6) or (7):



wherein R^7 represents a $\text{C}_1\text{-C}_{12}$ linear, branched or cyclic alkyl group or a $\text{C}_6\text{-C}_{20}$ aryl group; X represents a halogen atom or a hydrogen atom; and n is an integer of from 1 to 3; or



wherein R^7 is as defined for formula (6); Y represents an $-\text{OR}^8$ group, an $-\text{OSiR}_3^9$ group, an $-\text{AlR}_2^{10}$ group, an $-\text{NR}_2^{11}$ group, an $-\text{SiR}_3^{12}$ group or an $-\text{N}(\text{R}^{13})\text{AlR}_2^{14}$ group, wherein each of R^8 , R^9 , R^{10} and R^{14} independently represents a $\text{C}_1\text{-C}_{12}$ alkyl group or a $\text{C}_6\text{-C}_{20}$ aryl group, R^{11} represents a hydrogen group, a $\text{C}_1\text{-C}_{12}$ alkyl group, a $\text{C}_6\text{-C}_{20}$ aryl group or a silyl group which is unsubstituted or substituted with at least one $\text{C}_1\text{-C}_{12}$ alkyl group, and each of R^{12} and R^{13} independently represents a $\text{C}_1\text{-C}_{12}$ alkyl group, with the proviso that each alkyl group is independently of a linear, a branched or a cyclic configuration; and n is 1 or 2.

8. The method according to item 6 or 7 above, wherein, in the component (B), the particulate inorganic solid (b-1) having hydroxyl groups on the surface thereof is at least one member selected from the group consisting of SiO_2 , Al_2O_3 , MgO , ZrO_2 , TiO_2 , B_2O_3 , CaO , ZnO , BaO , V_2O_5 , Cr_2O_3 and ThO_2 .

9. The method according to item 6 or 7 above, wherein, in the component (B), the particulate inorganic solid (b-1) having hydroxyl groups on the surface thereof is silica.

10. The method according to any one of items 6 to 9 above, wherein, in copolymerizing ethylene, ethylene is copolymerized with at least one comonomer selected from the group consisting of a $\text{C}_3\text{-C}_{20}$ cyclic olefin, $\text{C}_4\text{-C}_{20}$ linear and cyclic dienes, $\text{C}_5\text{-C}_{20}$ branched dienes and an α -olefin represented by the formula $\text{H}_2\text{C}=\text{CHR}^{15}$ wherein R^{15} is methyl, ethyl, a $\text{C}_3\text{-C}_{18}$ linear, branched or cyclic alkyl group or a $\text{C}_6\text{-C}_{20}$ aryl group.

[0025] Hereinbelow, the high density ethylene polymer of the present invention is explained in detail.

[0026] The high density ethylene polymer of the present invention essentially comprises a homopolymer of ethylene, or a copolymer of ethylene with at least one comonomer selected from the group consisting of an α -olefin, a cyclic olefin, and linear, branched and cyclic dienes. More particularly, the high density ethylene polymer of the present invention comprises a homopolymer of ethylene, or a copolymer of ethylene with at least one comonomer selected from the group consisting of an α -olefin represented by the formula $\text{H}_2\text{C}=\text{CHR}^{15}$ wherein R^{15} represents methyl, ethyl, a $\text{C}_3\text{-C}_{18}$ linear, branched or cyclic alkyl group or a $\text{C}_6\text{-C}_{20}$ aryl group; a $\text{C}_3\text{-C}_{20}$ cyclic olefin, $\text{C}_4\text{-C}_{20}$ linear, and cyclic dienes, and $\text{C}_5\text{-C}_{20}$ branched dienes.

[0027] When the high density ethylene polymer of the present invention is a copolymer of ethylene with at least one comonomer, the content of the comonomer units in the high density ethylene copolymer is preferably 1 mole % or less, more preferably 0.5 mole % or less, still more preferably 0.2 mole % or less, still more preferably 0.1 mole % or less, based on the total number of moles of all monomer units constituting the ethylene polymer. When the content of the comonomer units exceeds 1 mole %, the density of the ethylene copolymer is markedly lowered, so that practical

problems, such as a lowering of stiffness, are likely to arise.

[0028] The high density ethylene polymer of the present invention has a density d (g/cm³) of not lower than 0.951. When the density of the high density ethylene polymer is lower than 0.951 g/cm³, practical problems arise, such that the polymer does not have a satisfactorily high stiffness. The high density ethylene polymer of the present invention, which has a density of not lower than 0.951 g/cm³, exhibits a satisfactorily high stiffness from the practical viewpoint. The density of the high density ethylene polymer of the present invention is preferably not lower than 0.955 g/cm³, more preferably not lower than 0.960 g/cm³, still more preferably not lower than 0.965 g/cm³.

[0029] On the other hand, the density of the high density ethylene polymer of the present invention is not higher than 0.980 g/cm³. When the density of the high density ethylene polymer is higher than 0.980 g/cm³, the polymer has an excessively high degree of crystallinity, so that the polymer is likely to suffer brittle fracture, which is practically disadvantageous. It is preferred that the density of the high density ethylene polymer of the present invention be not higher than 0.975 g/cm³.

[0030] In the present invention, the density of an ethylene polymer is measured as follows. A polymer strand, which has been obtained in the operation of the measurement of the MFR of the ethylene polymer at 190 °C under a load of 2.16 kg, is heated at 120 °C for 1 hour and then, gradually cooled to room temperature. The cooled strand is subjected to a density measurement by means of a density-gradient tube.

[0031] The high density ethylene polymer of the present invention has an Izod impact strength of 1 kgf-cm/cm² or more, and satisfies the following relationship:

$$\log a_{kl} \geq -0.844 \log M_i + 1.462$$

wherein a_{kl} represents the Izod impact strength (kgf-cm/cm²), and M_i represents the melt flow rate as measured at 190 °C under a load of 2.16 kg.

[0032] It is preferred that the high density ethylene polymer of the present invention satisfies the following relationship:

$$\log a_{kl} \geq -0.844 \log M_i + 1.575$$

wherein a_{kl} and M_i are as defined above.

[0033] It is more preferred that the high density ethylene polymer of the present invention satisfies the following relationship:

$$\log a_{kl} \geq -0.844 \log M_i + 1.700$$

wherein a_{kl} and M_i are as defined above.

[0034] In general, when the M_i of a polymer is increased, the polymer exhibits improved moldability, but the impact resistance of the polymer disadvantageously decreases. Therefore, when the M_i of a polymer is increased for the purpose of improving the moldability thereof, it has conventionally been attempted to decrease the density of the polymer by, for example, copolymerization, so as to prevent a lowering of the impact resistance of the polymer. However, the decrease in the density of an ethylene polymer, in turn, causes a lowering of the stiffness of the ethylene polymer, so that the application of such a density-decreasing technique is practically limited. By contrast, the high density ethylene polymer of the present invention surprisingly exhibits a satisfactorily high impact strength in spite of its high density.

[0035] In the present invention, Izod impact strength a_{kl} (kgf-cm/cm²) is measured in accordance with JIS K 7110.

[0036] The high density ethylene polymer of the present invention has an M_i (g/10 minutes) of more than 5 and not more than 100, wherein M_i is defined as the MFR as measured at 190 °C under a load of 2.16 kg.

[0037] When the high density ethylene polymer has an M_i of not more than 5, a marked lowering of the moldability thereof occurs, so that the ethylene polymer cannot be practically employed as a material for injection molding and the like. The high density ethylene polymer of the present invention has an M_i of more than 5, so that it exhibits an excellent moldability. In a preferred embodiment of the present invention, the high density ethylene polymer has an M_i of preferably more than 10.

[0038] Further, the high density ethylene polymer of the present invention has an M_i of not more than 100. When the high density ethylene polymer has an M_i of more than 100, the ethylene polymer has an extremely poor impact resistance and hence cannot be practically used. For obtaining a more improved impact resistance, it is preferred that the high density ethylene polymer has an M_i of not more than 80, more preferably not more than 50, most preferably not more than 30.

[0039] The high density ethylene polymer of the present invention satisfies the following relationship:

$$\log M_{IR} \cong -0.094 \log M_I + 1.520$$

wherein M_I is as defined above, and M_{IR} represents the H_{MI}/M_I ratio in which H_{MI} (g/10 minutes) is defined as the MFR as measured at 190 °C under a load of 21.6 kg and M_I is as defined above.

[0040] By virtue of the M_I and M_{IR} which satisfy the above-mentioned relationship, the density of the high density ethylene polymer of the present invention can be satisfactorily high, so that improved mechanical properties, such as high stiffness, can be achieved.

[0041] In the present invention, when the high density ethylene polymer satisfies the following relationship:

$$\log M_{IR} \cong -0.125 \log M_I + 1.574,$$

the ethylene polymer can achieve a further improvement in the mechanical properties thereof, such as stiffness. Further, when the high density ethylene polymer satisfies the following relationship:

$$\log M_{IR} \cong -0.198 \log M_I + 1.698,$$

the ethylene polymer can achieve still a further improvement in the mechanical properties thereof.

[0042] In the present invention, M_I and H_{MI} are measured in accordance with the condition E and condition F of the ASTM D1238, respectively.

[0043] It is preferred that the high density ethylene polymer of the present invention has an H_{MI} of not less than 90 and not more than 5,000. In the present invention, it is more preferred that the ethylene polymer have an H_{MI} of not less than 140 and not more than 3,000.

[0044] Further, the high density ethylene polymer of the present invention has an M_{IR} of not less than 25 and not more than 40. In the present invention, it is preferred that the ethylene polymer has an M_{IR} of not less than 28, more preferably not less than 30.

[0045] In the high density ethylene polymer of the present invention, the density d (g/cm³) and the M_I (g/10 minutes) satisfy the following relationship:

$$d \cong -0.00873 \log M_I + 0.972.$$

[0046] As mentioned above, in general, when the M_I of a polymer is increased, the polymer exhibits an increased density and an improved moldability, but the impact resistance of the polymer is disadvantageously reduced. Therefore, when the M_I of a polymer is increased for the purpose of improving the moldability thereof, it has conventionally been attempted to decrease the density of the polymer by, for example, copolymerization, so as to prevent a lowering of the impact resistance of the polymer. However, the decrease in the density of an ethylene polymer, in turn, causes a lowering of the stiffness of the ethylene polymer, so that the application of such a density-decreasing technique is practically limited. The high density ethylene polymer of the present invention has a high impact resistance as compared to the conventional high density ethylene polymers. Therefore, even when the M_I of the high density ethylene polymer is increased, the high impact resistance remains satisfactory. There is no need for lowering the density of the ethylene polymer for achieving a satisfactory impact resistance. In addition, because the high density ethylene polymer of the present invention satisfies the above-mentioned relationship between the density and M_I , the ethylene polymer has an extremely good balance between various properties, such as stiffness, moldability and the like.

[0047] In a more preferred embodiment of the high density ethylene polymer of the present invention, the density d (g/cm³) and the M_I (g/10 minutes) satisfy the following relationship:

$$d \cong -0.00873 \log M_I + 0.976.$$

[0048] The high density ethylene polymer of the present invention has an M_w of 30,000 or more, wherein M_w is defined as a weight average molecular weight measured by gel permeation chromatography (GPC) using a calibration curve obtained with respect to a standard polystyrenes. It is also preferred that the high density ethylene polymer has an M_w of not more than 500,000, more preferably not more than 300,000, still more preferably not more than 150,000,

still more preferably not more than 100,000, most preferably not more than 80,000.

[0049] The high density ethylene polymer of the present invention has an Mw/Mn ratio of 5.0 or more, wherein Mw and Mn, respectively, represent the weight average molecular weight and the number average molecular weight, each measured by gel permeation chromatography (GPC) using a calibration curve obtained with respect to standard polystyrenes. An Mw/Mn ratio is generally used as a yardstick of molecular weight distribution. In general, the larger the Mw/Mn ratio, the broader the molecular weight distribution and the more improved the moldability. In the present invention, the Mw/Mn ratio is more preferably 5.5 or more, still more preferably 6.0 or more, most preferably 7.0 or more. On the other hand, in the present invention, the Mw/Mn ratio is not more than 10.0. When the Mw/Mn ratio is too large, various disadvantages, such as a lowering of impact resistance, are likely to arise. In the present invention, the Mw/Mn ratio is preferably not more than 9.5, more preferably not more than 9.0.

[0050] Hereinbelow, the molecular weight distribution of the high density ethylene polymer of the present invention will be described in detail.

[0051] In general, a molecular weight distribution curve of an ethylene polymer can be approximated by a Gaussian distribution curve. By using a computer, an optimized approximation of the molecular weight distribution curve can be achieved within a relatively short period of time. The approximation can be achieved using a single Gaussian distribution curve. However, in some cases, the precision of the approximation may be improved by overlapping a plurality of Gaussian distribution curves. When the molecular weight distribution curve is approximated by overlapping a plurality of Gaussian distribution curves, the plurality of Gaussian distribution curves may be regarded as being curves obtained by the resolution of the molecular weight distribution curve. In approximating the molecular weight distribution curve by the overlapping of a plurality of Gaussian distribution curves by using a computer, the results of the computer calculation for the optimization of the approximation may vary depending on the initial values set for the calculation and, hence, there is a defect such that the calculation is affected by arbitrariness to some extent. Nevertheless, this method is an effective method for approximately determining the shape of distribution curve showing the molecular weight distribution.

[0052] When the molecular weight distribution curve of the high density ethylene polymer of the present invention is approximated by the above-mentioned technique using a plurality of Gaussian distribution curves, the approximation can be performed by using at least two Gaussian distribution curves. It is recommended to use three Gaussian distribution curves in the approximation of the molecular weight distribution. In the present invention, when the molecular weight distribution curve is approximated by using three Gaussian distribution curves, the area of a peak having a maximum peak area is represented by S_m . When one or more peaks are present on the high molecular weight side relative to the peak having a maximum peak area, the total of the one or more peaks on the high molecular weight side relative to the peak having a maximum peak area is represented by S_h . When one or more peaks are present on the low molecular weight side relative to the peak having a maximum peak area, the total area of the one or more peaks on the low molecular weight side relative to the peak having a maximum peak area is represented by S_l . In the present invention, either S_h or S_l can be 0.

[0053] In approximating the molecular weight distribution curve by using three Gaussian distribution curves as mentioned above, the three Gaussian distribution curves may be established so that S_m , S_h and S_l satisfy the following relationships. That is, it is preferred that the ratio of S_h to S_m , i.e., S_h/S_m ratio, be less than 1, more preferably $2/3$ or less, still more preferably $1/2$ or less, still more preferably $1/3$ or less, still more preferably $1/5$ or less, most preferably $1/10$ or less. Further, it is preferred that the ratio of S_l to S_m , i.e., S_l/S_m ratio, be less than 1, more preferably $2/3$ or less, still more preferably $1/2$ or less, still more preferably $1/3$ or less, still more preferably $1/5$ or less, most preferably $1/10$ or less.

[0054] The molecular weight distribution curves can be easily obtained by gel permeation chromatography (GPC) by using, for example, 150-C ALC/GPC, manufactured and sold by Waters Assoc. Co., USA.

[0055] The high density ethylene polymer of the present invention may have a critical shear stress of 4×10^6 dyn/cm² or less, in terms of the minimum shear stress at which a gross melt fracture occurs.

[0056] The term "gross melt fracture" means a state such that a polymer strand produced in the measurement of MFR suffers a vigorous melt fracture which adversely affects all portions (not only the surface) of the strand, thus causing a volumetric change in the entire body of the strand. With respect to the critical shear stress in terms of the minimum shear stress at which a gross melt fracture occurs, reference can be made to, for example, International Patent Application Publication No. WO 93/08221.

[0057] In the high density ethylene polymer of the present invention, the critical shear rate in terms of the minimum shear rate at which a surface melt fracture occurs is not larger than 1.5 times that of a conventional high density ethylene polymer having the same M_i and Mw/Mn as those of the high density ethylene polymer of the present invention.

[0058] The high density ethylene polymer of the present invention can be produced, for example, by polymerizing ethylene or ethylene and a comonomer in the presence of an olefin polymerization catalyst comprising components (A), (B) and (C) described below.

[0059] Thus, in another aspect of the present invention, there is provided a method for producing a high density

ethylene polymer of item 1 or 2 above, which comprises homopolymerizing ethylene or copolymerizing ethylene with at least one comonomer selected from the group consisting of an α -olefin, a cyclic olefin, and linear, branched and cyclic dienes, in the presence of a catalyst comprising the following components (A), (B) and (C):

- 5 (A) a transition metal compound represented by the formula (1)




10 wherein:

M represents a transition metal selected from the group consisting of zirconium, titanium and hafnium; each of R^1 and R^2 independently represents:

15 an indenyl group which is unsubstituted or substituted with at least one substituent selected from the group consisting of a C_1 - C_{20} alkyl group, a C_6 - C_{20} aryl group, an aralkyl group having a C_1 - C_{20} alkyl group substituted with at least one C_6 - C_{20} aryl group, and an alkylaryl group having a C_6 - C_{20} aryl group substituted with at least one C_1 - C_{20} alkyl group, wherein each alkyl group is independently of a linear, a branched or a cyclic configuration and wherein at least one carbon atom of the at least one substituent is optionally replaced by a silicon atom, the substituted indenyl group optionally having a substitution in which at least two positions thereof together are substituted with one substituent group, having a valence of two or more, derived from a substituent selected from the at least one substituent, the substituted indenyl group optionally having at least one substituent thereof bonded thereto through an oxygen, a nitrogen, a sulfur or a phosphorus atom,

25 each of R^3 and R^4 independently represents a hydrogen atom, a halogen atom, a C_1 - C_{20} alkyl group, a C_6 - C_{20} aryl group, an aralkyl group having a C_1 - C_{20} alkyl group substituted with at least one C_6 - C_{20} aryl group, an alkylaryl group having a C_6 - C_{20} aryl group substituted with a C_1 - C_{20} alkyl group, or a $-SO_3R^5$ group wherein R^5 is a C_1 - C_8 hydrocarbon group which is unsubstituted or substituted with at least one halogen atom, wherein each alkyl group is independently of a linear, a branched or a cyclic configuration and wherein at least one carbon atom of at least one of the alkyl, aryl, aralkyl and alkylaryl groups is optionally replaced by a silicon atom; and
each of R^1 , R^2 , R^3 and R^4 is bonded to the transition metal M;

- 35 (B) an inorganic solid component comprising a particulate inorganic solid (b-1) having hydroxyl groups on a surface thereof and, carried thereon, an organoaluminumoxy compound (b-2) having repeating alkyloxyaluminum units each represented by the formula (5)



- 45 wherein R^6 represents a C_1 - C_{12} linear, branched or cyclic alkyl group; and
(C) an organoaluminum compound

50 wherein components (B) and (C) are intimately mixed and contacted with each other to form an intimate mixture of components (B) and (C), and the intimate mixture and component (A) are separately introduced into a system for homopolymerizing or copolymerizing ethylene, followed by polymerization.

55 [0060] In the present invention, by using the above-mentioned olefin polymerization catalyst comprising the above-mentioned specific transition metal compound, it has become possible to obtain the high density ethylene polymer of the present invention, which has various excellent properties as mentioned above. This is completely unexpected from conventionally known techniques, and very surprising. The reason why such a high density ethylene polymer having excellent properties can be obtained by the use of the above-mentioned catalyst has not yet been elucidated. However, the present inventors consider that the reason for this is as follows. The so-called "metallocene catalyst" is also called

a "single site catalyst". The single site catalyst has a single active species (the term "active species" means the type of a site which exhibits a catalytic activity, namely, an active site of the catalyst.). It has conventionally been known that, when the polymerization is conducted using such a conventional metallocene catalyst, the resultant polymer has a very narrow molecular weight distribution. However, by use of the above-mentioned catalyst comprising the specific transition metal compound (A), it has unexpectedly become possible to obtain a polymer having a molecular weight distribution which is broader than that of the polymer obtained using a conventional metallocene catalyst. This is presumed to be ascribed to the characteristic features of the above-mentioned catalyst, wherein the transition metal compound (A) can have at least two stereoisomeric configurations, and that the catalyst further comprises the inorganic solid component (B) and the organoaluminum compound (C). It is presumed that, due to this slightly broader molecular weight distribution, a good balance of the properties of the high density ethylene polymer, such as impact resistance, stiffness and moldability has been successfully achieved. However, as mentioned above, the specific reasons for this have not yet been elucidated.

[0061] Hereinbelow, detailed explanation is made on a method for producing the high density ethylene polymer of the present invention.

[0062] The term "polymerization" used herein frequently means not only homopolymerization but also copolymerization, and the term "polymer" used herein frequently means not only a homopolymer but also a copolymer. The term "polymerization" used herein is not intended to include a preliminary polymerization [(i.e., prepolymerization) which is conventionally carried out, prior to a polymerization for obtaining a final polymer, for the purpose of, for example, controlling the particle size or powder characteristics of a polymer, or alleviating a reduction in catalyst activity], but means only a full polymerization which is carried out for producing a polymer as a final product. The full polymerization is carried out under reaction conditions, including a reaction temperature and a reaction pressure, which are preferred from the commercial and economical points of view. Such a reaction temperature is generally 50 °C or more, preferably 60 °C or more, and such a reaction pressure is generally 2 kg/cm² or more, preferably 5 kg/cm² or more.

[0063] In the catalyst used in the method of the present invention for producing a high density ethylene polymer, component (A) represented by formula (1) may have a halogen atom as a substituent. Examples of such a halogen atom include fluorine, chlorine, bromine and iodine.

[0064] In the ligand represented by the formula -SO₃R⁵ which is an example of a substituent in component (A) of formula (1), R⁵ is a C₁-C₈ hydrocarbon group, preferably a C₁-C₈ linear, branched or cyclic alkyl group or a C₆-C₈ aryl group, which is unsubstituted or substituted with at least one halogen atom. Specific examples of ligands represented by the formula -SO₃R⁵ include a p-toluenesulfonato group, a methanesulfonato group, a trifluoromethanesulfonato group and the like.

[0065] It is preferred that the transition metal compound used as component (A) can assume two or more stereoisomeric configurations.

[0066] It is preferred that each of R³ and R⁴ be independently an alkyl group, an aryl group, a halogen atom or the like.

[0067] Examples of transition metal compounds of formula (1), wherein M represents zirconium, include:

bis(indenyl)zirconium dichloride,
bis(methylindenyl)zirconium dichloride,
bis(ethylindenyl)zirconium dichloride,
bis(propylindenyl)zirconium dichloride,
bis(butylindenyl)zirconium dichloride,
bis(pentylindenyl)zirconium dichloride,
bis(hexylindenyl)zirconium dichloride,
bis(octylindenyl)zirconium dichloride,
bis(phenylindenyl)zirconium dichloride,
bis(methylphenylindenyl)zirconium dichloride,
bis(ethylphenylindenyl)zirconium dichloride,
bis(naphthylindenyl)zirconium dichloride,
bis(methylnaphthylindenyl)zirconium dichloride,
bis(dimethylindenyl)zirconium dichloride,
bis(dimethylpropylindenyl)zirconium dichloride,
bis(methylethylindenyl)zirconium dichloride,
bis(dimethylphenylindenyl)zirconium dichloride,
bis(tolylindenyl)zirconium dichloride,
bis(methyltolylindenyl)zirconium dichloride,
bis(indenyl)zirconium dibromide,
bis(indenyl)zirconium bis(p-toluenesulfonato),
bis(4,5,6,7-tetrahydroindenyl)zirconium dichloride,

bis(benzoindenyl)zirconium dichloride,
bis(methylbenzoindenyl)zirconium dichloride, and
bis(dimethylbenzoindenyl)zirconium dichloride.

[0068] When the above-mentioned transition metal compound has a substituent bonded to the indenyl ring, the substituent can be bonded to the ring at an arbitrary position thereof.

[0069] Further, alkyl groups, such as a propyl group or a butyl group, include isomers thereof, such as n-, iso-, sec- and tert-isomers thereof.

[0070] In the present invention, those transition metal compounds, which have the same structures as those of the above-mentioned zirconium compounds of formula (1) except that the zirconium is replaced by titanium or hafnium, can also be employed.

[0071] With respect to component (B) of the catalyst used in the present invention, it is preferred that particulate inorganic solid (b-1) having hydroxyl groups on the surface thereof [hereinbelow, frequently referred to simply as "particulate inorganic solid (b-1)" or "component (b-1)"] have a pore volume (PV: cm³/g) of from 0.4 to 1.4 cm³/g and a specific surface area (SA: m²/g) of from 150 to 800 m²/g, with the proviso that the pore volume (PV: cm³/g) and the specific surface area (SA: m²/g) satisfy the following relationship.

$$SA \leq -625 \times PV + 1100 \quad (2)$$

[0072] As mentioned above, in the catalyst used in the present invention, it is preferred that the particulate inorganic solid (b-1) have a pore volume (PV: cm³/g) of from 0.4 to 1.4 cm³/g.

[0073] When the pore volume of the particulate inorganic solid (b-1) is less than 0.4 cm³/g, the amount of an organoaluminumoxy compound carried on particulate inorganic solid (b-1) becomes very small so that the resultant catalyst cannot exhibit a satisfactorily high polymerization activity. Therefore, in the present invention, the pore volume of the particulate inorganic solid (b-1) is generally not less than 0.4 cm³/g, preferably not less than 0.5 cm³/g, more preferably not less than 0.6 cm³/g.

[0074] When the pore volume of the particulate inorganic solid (b-1) is more than 1.4 cm³/g, the total volume of voids in particulate inorganic solid (b-1) becomes very large, so that it becomes difficult to obtain a particulate inorganic solid having satisfactorily high mechanical strength. In this case, the particulate inorganic solid is likely to be broken into dust during the polymerization, so that the resultant polymer contains dust formed from the breakage of the particulate inorganic solid. As a result, various disadvantages are likely to be caused such that the powder characteristics of the polymer become poor, and that the bulk density of the polymer becomes low. Therefore, in the present invention, the pore volume of the particulate inorganic solid (b-1) is generally not more than 1.4 cm³/g, preferably not more than 1.2 cm³/g, more preferably not more than 1.1 cm³/g, most preferably not more than 1.0 cm³/g.

[0075] In the present invention, it is preferred that the particulate inorganic solid (b-1) has a specific surface area (SA: m²/g) of from 150 to 800 m²/g.

[0076] When the specific surface area of the particulate inorganic solid (b-1) is less than 150 m²/g, the amount of an organoaluminumoxy compound carried on the particulate inorganic solid (b-1), per unit weight of the particulate inorganic solid (b-1), becomes very small, so that the polymerization activity per unit weight of the particulate inorganic solid is likely to become low. Therefore, in the present invention, the specific surface area of the particulate inorganic solid (b-1) is generally not less than 150 m²/g, preferably not less than 200 m²/g, more preferably not less than 250 m²/g.

[0077] When the specific surface area of the particulate inorganic solid (b-1) is more than 800 m²/g, it becomes difficult to perform a uniform polymerization reaction over the entire surface of the catalyst. In this case, it is likely that a vigorous polymerization reaction locally occurs in the surface of the catalyst. As a result, various disadvantages are likely to be caused, such that the powder characteristics of the resultant polymer become poor, and that the bulk density of the polymer becomes low. Therefore, in the present invention, the specific surface area of particulate inorganic solid (b-1) is generally not more than 800 m²/g, preferably not more than 700 m²/g, more preferably not more than 600 m²/g.

[0078] Further, in the present invention, it is preferred that the particulate inorganic solid (b-1) has a pore volume (PV: cm³/g) and a specific surface area (SA: m²/g) within the above-mentioned respective ranges, with the proviso that the pore volume (PV: cm³/g) and the specific surface area (SA: m²/g) satisfy the following relationship.

$$SA \leq -625 \times PV + 1100 \quad (2)$$

[0079] For example, in the case of particulate silica having a pore volume (PV: cm³/g) of 1.0 cm³/g and a specific surface area (SA: m²/g) of 300 m²/g, the value of the right side of formula (2) is 475, and the value of the left side of formula (2) is 300. Therefore, the pore volume and specific surface area of this particulate silica satisfy the relationship

of formula (2).

[0080] When the pore volume (PV: cm³/g) and the specific surface area (SA: m²/g) of the silica do not satisfy the relationship of formula (2), it is likely that the silica suffers fine cracking. The cracks continue to grow during the polymerization, leading to a breakage of the silica, so that the resultant polymer contains dust formed from the breakage of the silica. As a result, various disadvantages are likely to be caused, such that the powder characteristics of the polymer are lowered to a commercially undesirable level and, in some cases, the bulk density of the polymer becomes considerably low.

[0081] Therefore, when particulate silica is used as the particulate inorganic solid (b-1) of the catalyst used in the present invention, it is preferred that the pore volume (PV: cm³/g) and the specific surface area (SA: m²/g) of the silica satisfy the relationship of formula (2), more preferably the relationship of the following formula (3):

$$SA \leq -625 \times PV + 1000 \quad (3).$$

[0082] As mentioned above, particulate inorganic solid (b-1) of the catalyst used in the present invention has hydroxyl groups on the surface thereof.

[0083] In the present invention, the hydroxyl groups on the surface of the particulate inorganic solid (b-1) are OH groups which are strongly bonded to the surface of the particulate inorganic solid even under polymerization conditions, and which, when heated at high temperatures, react with one another to generate H₂O. Such hydroxyl groups are not simply adsorbed onto the surface of the particulate inorganic solid (b-1) but are chemically bonded to the surface matrix of the particulate inorganic solid (b-1). For example, when silica having hydroxyl groups on the surface thereof is used as particulate inorganic solid (b-1), it is considered that each hydroxyl group forms an Si-OH bond with a silicon atom of the silica. The hydroxyl group having such a chemical bond is not easily liberated from the silica, even when, for example, contacted with an inert solvent.

[0084] In the present invention, the hydroxyl group content of the particulate inorganic solid (b-1) is determined by subjecting the particulate inorganic solid to heat treatment at 1000 °C under atmospheric pressure. The hydroxyl group content of particulate inorganic solid (b-1) is determined as a ratio (% by weight) of the weight decrease of the particulate inorganic solid which is caused by the heat treatment, relative to the weight of the particulate inorganic solid before the heat treatment.

[0085] In the present invention, it is preferred that the hydroxyl group content of the particulate inorganic solid (b-1) be sufficient for bonding the organoaluminumoxy compound (b-2) having alkyl groups to the particulate inorganic solid (b-1). When the hydroxyl group content is too large relative to the amount of the organoaluminumoxy compound (b-2), the alkyl groups in the organoaluminumoxy compound (b-2) are destroyed by the hydroxyl groups, so that the resultant catalyst cannot exhibit a satisfactory catalytic activity. When the hydroxyl group content is too small, the bonding of the organoaluminumoxy compound to the particulate inorganic solid cannot be effectively performed. With respect to the mechanism of the bonding between the particulate inorganic solid (b-1) and the organoaluminumoxy compound (b-2), it is considered that a hydroxyl group on the particulate inorganic solid (b-1) reacts with an alkyl group in the organoaluminumoxy compound (b-2) to form an O-Al bond, thereby performing the bond between (b-1) and (b-2). For example, when silica as the particulate inorganic solid (b-1) is contacted with methylaluminoxane as the organoaluminumoxy compound (b-2), the generation of methane gas is observed. The reason for the generation of methane gas can be explained as follows. A methyl group in methylaluminoxane reacts with a hydroxyl group (OH group) on the surface of the silica, to thereby form an O-Al bond and methane (CH₄) which is released in a gaseous form. Therefore, when the hydroxyl group content of the particulate inorganic solid (b-1) is too small relative to the amount of organoaluminumoxy compound (b-2), the number of O-Al bonds formed by the reaction of a hydroxyl group on the particulate inorganic solid (b-1) with an alkyl group in the organoaluminumoxy compound (b-2) also becomes too small, so that it becomes difficult to strongly bond a desired amount of the organoaluminumoxy compound (b-2) to the particulate inorganic solid (b-1). In the present invention, the molar ratio (OH/Al_{b-2}) of a hydroxyl group (OH group) on the surface of the particulate inorganic solid (b-1) to aluminum (Al_{b-2}) in organoaluminumoxy compound (b-2) is preferably in the range of from 0.01 to 1, more preferably from 0.05 to 0.7.

[0086] For bonding the organoaluminumoxy compound (b-2) to the particulate inorganic solid (b-1) in a necessary and effective amount for polymerization, the hydroxyl group content of the particulate inorganic solid (b-1) is preferably not less than 0.5 % by weight, more preferably not less than 1 % by weight. However, when the hydroxyl group content of the particulate inorganic solid (b-1) is too large, the polymerization activity of the resultant catalyst is likely to become low. The reason for this has not been elucidated yet, but is considered to be as follows. When the hydroxyl group content is too large, the sites for reaction with the alkyl groups in the organoaluminumoxy compound (b-2) are caused to be excessively present on the surface of the particulate inorganic solid (b-1), so that the effect of the organoaluminumoxy compound as an auxiliary catalyst for the polymerization is lowered. That is, when the hydroxyl group content on the surface of the particulate inorganic solid (b-1) is too large, the polymerization activity of the resultant catalyst is

likely to be lowered. Therefore, in the present invention, the upper limit of the hydroxyl group content is preferably 15 % by weight, more preferably 12 % by weight, most preferably 10 % by weight.

[0087] In the present invention, the hydroxyl group content of the particulate inorganic solid (b-1) can be adjusted to a predetermined level within the range of from 0.5 to 15 % by weight, by subjecting a particulate inorganic solid having hydroxyl groups on the surface thereof to heat treatment at an appropriate temperature. This heat treatment is advantageously employed when the hydroxyl group content of component (b-1) is more than 15 % by weight, or when it is desired to further lower the hydroxyl group content of component (b-1) having a hydroxyl group content of less than 15 % by weight. The heat treatment for adjusting the hydroxyl group content of particulate inorganic solid (b-1) is conducted preferably at 150 °C or more, more preferably 200 °C or more, and preferably 1000 °C or less, more preferably 800 °C or less.

[0088] In the present invention, also by contacting a particulate inorganic solid (b-1) having hydroxyl groups on the surface thereof with an organoaluminum compound, a particulate inorganic solid (b-1) having a hydroxyl group content adjusted to a predetermined level can be obtained. With respect to the temperature at which a particulate inorganic solid (b-1) having hydroxyl groups on the surface thereof is contacted with an organoaluminum compound, there is no particular limitation. However, it is preferred that the contact be conducted at room temperature or at an elevated temperature of 100 °C or less. The reason why the adjustment of the hydroxyl group content of a particulate inorganic solid (b-1) can be performed by contacting the particulate inorganic solid (b-1) with an organoaluminum compound is believed to reside in that the hydroxyl groups react with the organoaluminum compound, so that the hydroxyl groups are rendered chemically inactive.

[0089] In the present invention, the use of an organoaluminum compound also has an advantage in that the amount of the organoaluminumoxy compound (b-2) to be used can be reduced.

[0090] An example of the organoaluminum compounds which can be used in the present invention is one which is represented by the following formula (4):



wherein R^5 represents a C_1 - C_{12} linear, branched or cyclic alkyl group or a C_6 - C_{20} aryl group; X represents a halogen atom or a hydrogen atom; and

n is an integer of from 1 to 3.

[0091] Examples of R^5 in formula (4) include a methyl group, an ethyl group, an n-propyl group, an isopropyl group, an isobutyl group, a pentyl group, a hexyl group, an octyl group, a cyclopentyl group, a cyclohexyl group, a phenyl group and a tolyl group.

[0092] Specific examples of organoaluminum compounds defined above include a trialkylaluminum, such as trimethylaluminum, triethylaluminum, triisopropylaluminum, triisobutylaluminum, trioctylaluminum, or tri 2-ethylhexylaluminum; an alkenylaluminum, such as isoprenylaluminum; a dialkylaluminum halide, such as dimethylaluminum chloride, diethylaluminum chloride, diisopropylaluminum chloride, diisobutylaluminum chloride, or dimethylaluminum bromide; an alkylaluminum sesquihalide, such as methylaluminum sesquichloride, ethylaluminum sesquichloride, isopropylaluminum sesquichloride, butylaluminum sesquichloride, or ethylaluminum sesquibromide; an alkylaluminum dihalide, such as methylaluminum dichloride, ethylaluminum dichloride, isopropylaluminum dichloride, and ethylaluminum dibromide; and a dialkylaluminum hydride, such as diethylaluminum hydride, or diisobutylaluminum hydride.

[0093] In the present invention, when an organoaluminum compound is used for adjusting the hydroxyl group content of the surface of a particulate inorganic solid (b-1) to a predetermined level, the amount of the organoaluminum compound to be used is such as would provide an Al_R/OH molar ratio of 1 or less, wherein Al_R is the amount of the aluminum contained in the organoaluminum compound and OH is the amount of the hydroxyl groups on the surface of the particulate inorganic solid.

[0094] In the present invention, when an organoaluminum compound is used for adjusting the hydroxyl group content of the surface of a particulate inorganic solid (b-1) to a predetermined level, the adjustment is usually conducted by contacting the particulate inorganic solid (b-1) with the organoaluminum compound. The resultant particulate inorganic solid (b-1) having the hydroxy group content adjusted to a predetermined level is contacted with the organoaluminumoxy compound (b-2), thereby bonding the organoaluminumoxy compound (b-2) to the particulate inorganic solid (b-1). Alternatively, the adjustment can be conducted by contacting a particulate inorganic solid (b-1) with a mixture of organoaluminumoxy compound (b-2) and the organoaluminum compound, so that the bonding of the organoaluminumoxy compound (b-2) to the particulate inorganic solid (b-1) can be conducted, simultaneously with the adjustment of the hydroxyl group content of the particulate inorganic solid (b-1).

[0095] As mentioned above, when the adjustment of the hydroxyl group content of the particulate inorganic solid (b-1) is performed by heating without using an organoaluminum compound, the molar ratio (OH/Al_{b-2}) of a hydroxyl group

(OH group) on the surface of the particulate inorganic solid (b-1) to aluminum (Al_{b-2}) in organoaluminumoxy compound (b-2) is preferably in the range of from 0.01 to 1, more preferably from 0.05 to 0.7. When the organoaluminum compound is used in adjusting the hydroxyl group content of the surface of a particulate inorganic solid to a predetermined level, the sum of the molar amount of aluminum (Al_{b-2}) in organoaluminumoxy compound (b-2) and the molar amount of aluminum (Al_R) in the organoaluminum compound is taken as the molar amount of Al_{b-2} in calculating the molar ratio (OH/Al_{b-2}) of the hydroxyl groups (OH) on the surface of the particulate inorganic solid to the aluminum (Al_{b-2}) in organoaluminumoxy compound (b-2). Accordingly, in the present invention, when the organoaluminum compound is used in adjusting the hydroxyl group content of the surface of a particulate inorganic solid to a predetermined level, with respect to the molar ratio $[OH/(Al_{b-2} + Al_R)]$ of the hydroxyl groups (OH) on the surface of the particulate inorganic solid to the sum of the molar amount of aluminum (Al_{b-2}) in organoaluminumoxy compound (b-2) and the molar amount of aluminum (Al_R) in the organoaluminum compound, the upper limit is preferably 1, more preferably 0.7, and the lower limit is preferably 0.01, more preferably 0.05.

[0096] In the present invention, when an organoaluminum compound is used for adjusting the hydroxyl group content of the surface of a particulate inorganic solid to a predetermined level, the molar ratio (Al_R/Al_{b-2}) of the aluminum (Al_R) in the organoaluminum compound to the aluminum (Al_{b-2}) in organoaluminumoxy compound (b-2) is preferably 1 or less.

[0097] As described above, in the present invention, it is preferred that, the particulate inorganic solid (b-1) having hydroxyl groups on the surface thereof has a pore volume (PV: cm^3/g) of from 0.4 to 1.4 cm^3/g and a specific surface area (SA: m^2/g) of from 150 to 800 m^2/g , with the proviso that the pore volume (PV: cm^3/g) and the specific surface area (SA: m^2/g) satisfy the relationship represented by the formula (2).

$$SA \leq -625 \times PV + 1100 \quad (2)$$

By using a particulate inorganic solid (b-1) satisfying the above conditions, an organoaluminumoxy compound (b-2) can be especially strongly bonded to the particulate inorganic solid (b-1), and a polymer containing no very fine particles and exhibiting excellent powder characteristics and a high bulk density can be very effectively produced without conducting a preliminary polymerization.

[0098] As a material for the particulate inorganic solid (b-1), a particulate inorganic porous material is preferred. Examples of main components of particulate inorganic porous materials include oxides, such as SiO_2 , Al_2O_3 , MgO , ZrO_2 , TiO_2 , B_2O_3 , CaO , ZnO , BaO , V_2O_5 , Cr_2O_3 , and ThO_2 . These oxides are used individually or in mixture thereof, or in the form of a composite oxide thereof. Examples of such composite oxides include SiO_2 - MgO , SiO_2 - Al_2O_3 , SiO_2 - TiO_2 , SiO_2 - V_2O_5 , SiO_2 - Cr_2O_3 , and SiO_2 - TiO_2 - MgO . It is preferred that the main component of the material for the particulate inorganic solid (b-1) be at least one compound selected from the group consisting of SiO_2 , Al_2O_3 and MgO .

[0099] In the present invention, among the above-mentioned examples of materials for the particulate inorganic solid (b-1), a particulate silica composed mainly of SiO_2 is especially preferred.


[0100] With respect to a method for preparing such a particulate silica, there is no particular limitation, but a sol-gel process is preferred. In the present invention, the term "sol-gel process" means a process in which solation and gelation are conducted to obtain a particulate silica. The sol-gel process comprises, for example, reacting a solution of sodium silicate with sulfuric acid to form silicic acid, subjecting the formed silicic acid to polycondensation to thereby form a silicate polymer in the form of a colloidal silica (silica hydrosol), subjecting the obtained silica hydrosol to gelation to thereby obtain a silica hydrogel, and drying the silica hydrogel to thereby produce a silica xerogel. By combining such a sol-gel process with another process, such as a hydrothermal process, various properties of a particulate silica, such as a pore volume, a specific surface area, a particle morphology and a particle size, can be controlled relatively easily. It is also possible to control the chemical properties of the particulate silica by incorporating therein elements other than silicon, such as aluminum and titanium, in the form of individual oxides thereof. Therefore, in the present invention, a particulate silica may contain such additives, that is, aluminum oxide, titanium oxide and the like.

[0101] In the present invention, with respect to the shape of the particulate inorganic solid (b-1), there is no particular limitation, but a spherical shape is preferred. In the present invention, the term "spherical shape" means a shape which has no edges and is close to a sphere as a whole.

[0102] In the present invention, the average particle diameter of the particulate inorganic solid (b-1) is 5 μm or more, preferably 10 μm or more, and 200 μm or less, preferably 100 μm or less.

[0103] A particulate silica having such a spherical shape and such an average particle diameter can be obtained easily by the above-mentioned sol-gel process.

[0104] In the present invention, the organoaluminumoxy compound (b-2) [hereinbelow, frequently referred to simply as "component (b-2)"] is an aluminoxane having repeating alkylaluminumoxy units each represented by the formula (5)



(5)

wherein R⁶ represents a C₁-C₁₂ linear, branched or cyclic alkyl group.

[0105] Representative examples of R⁶ in the formula (5) include a methyl group, an ethyl group, an n-propyl group, an isopropyl group, an n-butyl group, an isobutyl group, a pentyl group, a hexyl group, an octyl group, a decyl group, a cyclohexyl group and a cyclooctyl group. Among these, a methyl group and an ethyl group are preferred, and a methyl group is especially preferred. Representative examples of organoaluminumoxy compounds having repeating alkylaluminumoxy units of a single type represented by the formula (5) include methylaluminoxane, ethylaluminoxane, n-propylaluminoxane, isopropylaluminoxane, n-butylaluminoxane, isobutylaluminoxane, pentylaluminoxane, hexylaluminoxane, octylaluminoxane, decylaluminoxane, cyclohexylaluminoxane and cyclooctylaluminoxane. Among these, methylaluminoxane, ethylaluminoxane and isobutylaluminoxane are preferred, and methylaluminoxane is especially preferred. In the present invention, the organoaluminumoxy compound having repeating alkylaluminumoxy units each represented by the formula (5) is not limited to an organoaluminumoxy compound having repeating alkylaluminumoxy units of one type represented by the formula (5), but may have two or more different types of repeating alkylaluminumoxy units each represented by the formula (5). Examples of such organoaluminumoxy compounds having two or more different types of repeating alkylaluminumoxy units each represented by the formula (5) include ethylmethylaluminoxane, methylpropylaluminoxane and butylmethylaluminoxane. The respective proportions of individual types of repeating alkylaluminumoxy units in such an organoaluminumoxy compound can be arbitrarily selected between 0 % and 100 %. A plurality of types of organoaluminumoxy compounds each having repeating alkylaluminumoxy units of a single type each represented by the formula (5), may be used in combination. Examples of such combinations include a mixture of methylaluminoxane and ethylaluminoxane, a mixture of methylaluminoxane and n-propylaluminoxane, and a mixture of methylaluminoxane and isobutylaluminoxane.

[0106] The degree of polymerization of an aluminoxane is generally from 2 to 100, preferably from 4 to 40.

[0107] In the present invention, the organoaluminumoxy compound (b-2) to be used as an auxiliary catalyst may contain unreacted chemical substances derived from the raw materials used in the synthesis of component (b-2). As is well known, an organoaluminumoxy compound is synthesized generally by reacting a trialkylaluminum with H₂O, and a part of these starting materials may remain unreacted. An organoaluminumoxy compound, which contains these unreacted materials in an amount of less than 50 % by weight, can be used as component (b-2). Specifically, for example, methylaluminoxane is synthesized by reacting trimethylaluminum with H₂O, and a part of at least one of these starting materials may remain unreacted and thus be contained in the obtained methylaluminoxane. In the above-mentioned synthesis method of an organoaluminumoxy compound, trialkylaluminum is generally used in an amount larger than that of H₂O so that the trialkylaluminum, as an unreacted material, tends to be contained in the obtained organoaluminumoxy compound. In the present invention, two or more types of trialkylaluminum may be contained in the organoaluminumoxy compound.

[0108] In the present invention, the inorganic solid component (B) [hereinbelow, frequently referred to simply as "component (B)"] comprising a particulate inorganic solid (b-1) having hydroxyl groups on the surface thereof and, carried thereon, an organoaluminumoxy compound (b-2), can be prepared by contacting the particulate inorganic solid (b-1) with the organoaluminumoxy compound (b-2). It is considered that, by the contacting, component (b-1) reacts with component (b-2).

[0109] Such a reaction can be easily advanced by mixing and heating the particulate inorganic solid (b-1) and the organoaluminumoxy compound (b-2) in an inert hydrocarbon medium.

[0110] Representative examples of such inert hydrocarbon media include aliphatic hydrocarbons, such as propane, butane, pentane, hexane, heptane, octane, decane, dodecane and kerosine; alicyclic hydrocarbons, such as cyclopentane, cyclohexane and methylcyclopentane; aromatic hydrocarbons, such as benzene, toluene and xylene; halogenated hydrocarbons, such as ethyl chloride, chlorobenzene and dichloromethane; and mixtures of them.

[0111] In mixing component (b-1) with component (b-2) in an inert hydrocarbon medium, it is preferred that the amount of component (b-2) be in the range of from 10⁻⁴ to 1 mol per g of component (b-1), more preferably from 10⁻³ to 10⁻¹ mol per g of component (b-1), and that the concentration of component (b-2) in the inert hydrocarbon medium be in the range from 5 x 10⁻² to 5 mol/liter, more preferably from 0.1 to 3 mol/liter.

[0112] In the present invention, the molar amount of component (b-2) is calculated on the assumption that one alkylaluminumoxy unit represented by formula (5) is one molecule. Therefore, 1 mol of component (b-2) contains 1 gram-atom of aluminum.

[0113] In mixing component (b-1) with component (b-2), the reaction temperature is generally in the range of from -50 to 150 °C, preferably from -20 to 120 °C. However, it is not necessary to maintain the temperature within the above

range during the mixing. Since the reaction of component (b-1) with component (b-2) is exothermic, it is preferred that the reaction temperature be controlled to a level as low as possible at the early stage of the reaction, and then elevated at the late stage of the reaction in order to complete the reaction. Specifically, the temperature at the early stage of the reaction is preferably in the range of from -50 to 50 °C, more preferably of from -20 to 30 °C, and the temperature at the late stage of the reaction is preferably in the range of from 50 to 150 °C, more preferably of from 60 to 120 °C. The contact time between component (b-1) and component (b-2) is generally in the range of from 0.5 to 100 hours, preferably from 1 to 50 hours.

[0114] In the present invention, the larger the atomic ratio (Al_{b-2}/M) of the aluminum (Al_{b-2}) in component (b-2) to the transition metal (M) in component (A), the higher the catalytic activity becomes, thus leading to an advantage from an economical view point. However, component (b-2) is generally expensive and, therefore, when the above-mentioned atomic ratio is excessively high, the economic advantage becomes rather low. Therefore, with respect to the atomic ratio (Al_{b-2}/M) of the aluminum (Al_{b-2}) in component (b-2) to the transition metal (M) in component (A), the upper limit is preferably 2,000, more preferably 1,000, most preferably 500, and the lower limit is preferably 10, more preferably 20, still more preferably 30, most preferably 100.

[0115] The amount of the organoaluminumoxy compound (b-2) carried on the particulate inorganic solid (b-1) is preferably in the range of from 0.5 to 500 mmol, more preferably from 1 to 50 mmol, most preferably from 3 to 30 mmol per g of component (b-1), in terms of the amount of aluminum (Al_{b-2}) in component (b-2).

[0116] In the present invention, examples of organoaluminum compound (C) [hereinbelow, frequently referred to simply as "component (C)"] include an organoaluminum compound represented by the formula (6)



wherein R^7 represents a C_1 - C_{12} linear, branched or cyclic alkyl group or a C_6 - C_{20} aryl group; X represents a halogen atom or a hydrogen atom; and n is an integer of from 1 to 3.

[0117] Representative examples of R^7 in the formula (6) include a methyl group, an ethyl group, an n-propyl group, an isopropyl group, an isobutyl group, a pentyl group, a hexyl group, an octyl group, a cyclopentyl group, a cyclohexyl group, a phenyl group and a tolyl group.

[0118] Illustrative examples of organoaluminum compounds of formula (6) include trialkylaluminums, such as trimethylaluminum, triethylaluminum, triisopropylaluminum, triisobutylaluminum, trioctylaluminum and tri-2-ethylhexylaluminum; alkenylaluminums, such as isoprenylaluminum; dialkylaluminum halides, such as dimethylaluminum chloride, diethylaluminum chloride, diisopropylaluminum chloride, diisobutylaluminum chloride and dimethylaluminum bromide; alkylaluminum sesquihalides, such as methylaluminum sesquichloride, ethylaluminum sesquichloride, isopropylaluminum sesquichloride, butylaluminum sesquichloride and ethylaluminum sesquibromide; alkylaluminum dihalides, such as methylaluminum dichloride, ethylaluminum dichloride, isopropylaluminum dichloride and ethylaluminum dibromide; and dialkylaluminum hydrides, such as diethylaluminum hydride and diisobutylaluminum hydride.

[0119] As another example of component (C), a compound represented by the following formula (7) can be mentioned:



wherein R^7 is as defined for formula (6); Y represents an $-OR^8$ group, an $-OSiR^9_3$ group, an $-OAlR^{10}_2$ group, an $-NR^{11}_2$ group, an $-SiR^{12}_3$ group or an $-N(R^{13})AlR^{14}_2$ group, wherein each of R^8 , R^9 , R^{10} and R^{14} independently represents a C_1 - C_{12} alkyl group or a C_6 - C_{20} aryl group, R^{11} represents a hydrogen atom, a C_1 - C_{12} alkyl group, a C_6 - C_{20} aryl group, or a silyl group which is unsubstituted or substituted with at least one C_1 - C_{12} alkyl group, and each of R^{12} and R^{13} independently represents a C_1 - C_{12} alkyl group, with the proviso that each alkyl group independently possesses a linear, a branched or a cyclic configuration; and n is 1 or 2.

[0120] Illustrative examples of organoaluminum compounds represented by formula (7) include the following compounds:

(i) compounds represented by the formula: $R^7_n Al(OR^8)_{3-n}$ (for example, dimethylaluminum methoxide, diethylaluminum ethoxide and diisobutylaluminum methoxide and the like);


(ii) compounds represented by the formula: $R^7_n Al(OSiR^9_3)_{3-n}$ [for example, $Et_2Al(OSiMe_3)$, $(iso-Bu)_2Al(OSiMe_3)$, $(iso-Bu)_2Al(OSiEt_3)$ and the like];

(iii) compounds represented by the formula: $R^7_n Al(OAlR^{10}_2)_{3-n}$ [for example, $Et_2AlOAlEt_2$, $(iso-Bu)_2AlOAl(iso-Bu)_2$ and the like];

(iv) compounds represented by the formula: $R^7_nAl(NR^{11})_{3-n}$ [for example, Me_2AlNEt_2 , $Et_2AlNHMe$, $Me_2AlNHEt$, $Et_2AlN(SiMe_3)_2$, $(iso-Bu)_2AlN(SiMe_3)_2$ and the like];

(v) compounds represented by the formula: $R^7_nAl(SiR^{12})_{3-n}$ [for example, $(iso-Bu)_2AlSiMe_3$ and the like]; and

(vi) compounds represented by the formula:



[for example,



and the like].

[0121] In the above formulae, Me, Et and Bu represent a methyl group, an ethyl group and a butyl group, respectively.

[0122] Of the organoaluminum compounds represented by formula (6) and those represented by formula (7), R^7_3Al , $R^7_nAl(OR^8)_{3-n}$ and $R^7_nAl(OAIR^{10})_{3-n}$ are preferred. Further, each of these compounds, wherein R^7 is an isoalkyl group and n is 2 or 3, is especially preferred. The above organoaluminum compounds can be used individually or in any combination.

[0123] In the present invention, the atomic ratio (Al_c/Al_{b-2}) of aluminum (Al_c) in the organoaluminum compound (C) to aluminum (Al_{b-2}) in the organoaluminumoxy compound (b-2) is generally from 0.01 to 5, preferably from 0.02 to 3.

[0124] In the present invention, by the use of the organoaluminum compound (C) in the polymerization catalyst, a high polymerization activity can be achieved. The reason for this is considered to reside in that component (C) facilitates the alkylation of component (A). Further explanation is made below with respect to this effect achieved by the use of component (C).

[0125] In the preparation of a catalyst, when a particulate inorganic solid (b-1) having the hydroxyl group content adjusted to a predetermined level which is prepared by contacting a particulate inorganic solid having hydroxyl groups on the surface thereof with an organoaluminum compound is used, a polymerization activity can be exerted to some extent, even without separately adding organoaluminum compound (C). The reason for this is considered to reside in that, due to some factors, such as non-uniformity of the reaction [for preparing component (B)] between the particulate inorganic solid and the organoaluminum compound, the resultant reaction mixture contains the unreacted organoaluminum compound which facilitates the alkylation of the transition metal compound. However, for obtaining a catalyst capable of effectively and stably exerting high polymerization activity, the use of a separate component (C) of the polymerization catalyst as defined in the present invention is required. One of the reasons for this resides in that, by use of component (C) in the polymerization catalyst, it becomes possible to neutralize or negate impurities which adversely affect the polymerization. Such neutralization or negation is practically equivalent to elimination of the impurities. Therefore, the catalyst can stably exert satisfactorily high polymerization activity during the polymerization. Furthermore, component (C) is effective for suppressing aggregation of the polymer. The reason for this is considered to reside in that component (C) serves to suppress generation of static electricity during the polymerization. However, the exact mechanism of the aggregation suppression has not yet been fully elucidated.

[0126] By use of the above-mentioned olefin polymerization catalyst comprising components (A), (B) and (C) described above, the homopolymerization of ethylene or the copolymerization of ethylene with a comonomer can be advantageously carried out to thereby obtain the high density ethylene polymer of the present invention.

[0127] With respect to the method for producing the high density ethylene polymer of the present invention, which is conducted in the presence of the olefin polymerization catalyst comprising the above-mentioned components (A), (B) and (C), detailed explanation is made below.

[0128] As to how to combine components (A), (B) and (C) and form the olefin polymerization catalyst to be used in a system for homopolymerizing or copolymerizing ethylene, there can be mentioned a method in which an intimate mixture of components (B) and (C) is formed, and the intimate mixture and component (A) are separately introduced

into the system for homopolymerizing or copolymerizing ethylene, to thereby effect the polymerization reaction.

[0129] This method is advantageous not only in that a high polymerization activity can be achieved, but also in that such a high polymerization activity can be stably maintained during the polymerization.

[0130] In the method for producing the high density ethylene polymer of the present invention, when ethylene is copolymerized with a comonomer, the comonomer is generally used in an amount of not more than 1 mol %, preferably not more than 0.5 mol %, more preferably not more than 0.2 mol %, still more preferably not more than 0.1 mol %, based on the total amount of ethylene and the comonomer. When a comonomer is used in an amount of more than 1 mol %, based on the total amount of ethylene and the comonomer, the resultant copolymer is likely to have a disadvantageously low density, so that practical problems, such as lowering of the stiffness of the copolymer, are likely to arise.

[0131] In the present invention, it is preferred that the high density ethylene polymer be produced by homopolymerizing ethylene or copolymerizing ethylene with at least one comonomer selected from the group consisting of an α -olefin represented by the formula $H_2C = CHR^{15}$ (wherein R^{15} is methyl, ethyl, a C_3 - C_{18} linear, branched or cyclic alkyl group or a C_6 - C_{20} aryl group), a C_3 - C_{20} cyclic olefin, a C_4 - C_{20} linear or cyclic diene, and a C_5 - C_{20} branched diene, in the presence of the above-mentioned polymerization catalyst comprising components (A), (B) and (C).

[0132] Examples of α -olefins represented by the formula $H_2C = CHR^{15}$ (wherein R^{15} is as defined above include propylene, 1-butene, 1-pentene, 1-hexene, 4-methyl-1-pentene, 1-octene, 1-decene, 1-dodecene, 1-tetradecene, 1-hexadecene, 1-octadecene, 1-eicosene, vinylcyclohexane and styrene. Examples of C_3 - C_{20} cyclic olefins include cyclopentene, cycloheptene, norbornene, 5-methyl-2-norbornene, tetracyclododecene and 2-methyl-1,4,5,8-dimethano-1,2,3,4,4a,5,8a-octahydronaphthalene. Examples of C_4 - C_{20} dienes include 1,3-butadiene, 1,4-pentadiene, 1,5-hexadiene, 1,4-hexadiene and cyclohexadiene.

[0133] The density and properties of the ethylene polymer can be controlled by appropriately selecting a comonomer from the above-mentioned comonomers, and copolymerizing ethylene with the comonomer.

[0134] In the present invention, the polymerization and copolymerization of ethylene can be conducted by either a suspension polymerization method or a gaseous phase polymerization method.

[0135] When a suspension polymerization is employed, the same solvent as the above-mentioned inert hydrocarbon solvents usable for preparing component (B) can be used. A certain olefin can also be used as the solvent.

[0136] In the polymerization method of the present invention using the above-mentioned polymerization catalyst, it is preferred that the amount of the catalyst fed to the system for homopolymerizing or copolymerizing ethylene be controlled so that the amount of component (B) becomes 1 to 0.001 % by weight, relative to the total weight of the polymer obtained per hour. The polymerization temperature is generally not lower than 0 °C, preferably not lower than 50 °C, more preferably not lower than 60 °C, and, on the other hand, generally not higher than 150 °C, preferably not higher than 110 °C, more preferably not higher than 100 °C. The polymerization pressure is generally from atmospheric pressure to 100 kg/cm², preferably from 2 to 50 kg/cm², more preferably from 5 to 30 kg/cm². The polymerization reaction can be conducted in a batchwise, a semi-continuous or a continuous manner. Further, the polymerization reaction can be conducted in at least two stages, wherein the respective reaction conditions in the two stages are different from each other.

[0137] The molecular weight of the ethylene polymer can be controlled by introducing hydrogen gas into the polymerization reaction system or by controlling the polymerization temperature (see, for example, DE 3127133.2). For example, by maintaining a predetermined amount ratio of the introduced hydrogen gas to the ethylene in the polymerization reaction system during the reaction, a high density ethylene polymer having a predetermined molecular weight can be easily obtained. In the present invention, it is recommended to control the molecular weight of the high density ethylene polymer by the above-mentioned method in which a predetermined amount ratio of the introduced hydrogen gas to the ethylene is maintained in the polymerization reaction system during the reaction.

[0138] In the present invention, the olefin polymerization catalyst can contain other components than mentioned above, which have favorable effects on the olefin polymerization.

BEST MODE FOR CARRYING OUT THE INVENTION

[0139] The present invention will now be further illustrated in more detail with reference to the following Examples and Comparative Examples, which should not be construed as limiting the scope of the present invention.

Example 1

[Preparation of a suspension of silica having methylaluminoxane carried thereon]

[0140] In a 200 ml glass flask which had been fully purged with nitrogen gas were placed 4.0 g of silica (which is manufactured and sold by Fuji Silysia Chemical Ltd., Japan, and has a pore volume of 1.10 cm³/g, a specific surface

area of 318 m²/g, a bulk density of 0.38 g/cm³ and a hydroxyl group content of 4.1 % by weight) and 40 ml of toluene, and stirring was conducted to obtain a suspension. The obtained suspension was cooled to -10 °C. To the cooled suspension was dropwise added 30 ml of a solution of methylaluminoxane (manufactured by Albemarle Corporation, U.S.A.) in toluene (Al concentration: 1.0 mol/liter) over 1 hour, while maintaining the temperature of the suspension at -10 °C. The temperature of the resultant mixture was maintained at 0 °C for 1 hour, then at room temperature for 1 hour, and then, at 110 °C for 3 hours, to thereby effect a reaction. During a series of the above operations, generation of methane gas from the mixture was observed. Then, the mixture was cooled to 20 °C, so that a suspension of silica having methylaluminoxane (MAO) carried thereon was obtained.

[Polymerization]

[0141] In a 1.6 liter stainless autoclave as a polymerizer, which had been fully purged with nitrogen gas, was placed 0.8 liter of hexane. Then, to the autoclave was added 0.2 mmol of triisobutylaluminum and further added the above-prepared silica suspension in an amount of 0.3 mmol in terms of the amount of aluminum of methylaluminoxane carried on the silica. Then, to the polymerizer was introduced 10 N ml of hydrogen and further introduced ethylene, so that the internal pressure of the polymerizer became 7 kg/cm²-G. The internal temperature of the polymerizer was adjusted to 65 °C.

[0142] A solution of bis(indenyl)zirconium dichloride in toluene (concentration: 2.5 mmol/liter) was introduced to the polymerizer in an amount of 1.0 μmol in terms of the amount of zirconium and, immediately after that, the internal temperature of the polymerizer was elevated to 70 °C, to thereby start a polymerization reaction of the ethylene.

[0143] The polymerization reaction was carried out while maintaining the temperature at 70 °C and maintaining the internal pressure of the polymerizer at 7 kg/cm²-G by supplying ethylene gas to the polymerizer. Hydrogen was introduced to the polymerizer, in an amount of 130 ml (NTP) relative to 1 kg/cm²-G of the consumed ethylene. The polymerization reaction was continued until the total amount of the consumed ethylene reached 1.5 kg/cm²-G.

[0144] After completion of the polymerization reaction, the reaction mixture obtained in the polymerizer was transferred to a stainless container containing methanol. The resultant mixture was subjected to filtration to thereby obtain a polymer. The obtained polymer was dried at 50 °C overnight.

[0145] The polymerizer was opened, and the inside thereof was examined. No polymer adhering to the inner wall and the like of the polymerizer was observed.

[0146] The reaction conditions and results of the polymerization are shown in Tables 1 and 2.

[0147] With respect to the obtained polymer, the relationship between the M_i and the Izod impact strength, the relationship between the M_i and the density (d) and the relationship between the M_i and the M_{iR} are shown in Figs. 1 to 3, respectively.

[0148] Further, with respect to the obtained polymer, the molecular weight distribution curve and a plurality of Gaussian distribution curves obtained by the resolution of the molecular weight distribution curve are shown in Fig. 4.

Examples 2 to 5

[0149] Polymerization reactions were individually conducted in substantially the same manner as in Example 1, except that the total amount of hydrogen introduced to the polymerizer was varied.

[0150] The reaction conditions and results of the polymerization are shown in Tables 1 and 2.

[0151] With respect to each of the obtained polymers the relationship between the M_i and the Izod impact strength, the relationship between the M_i and the density (d), and the relationship between the M_i and the M_{iR} are shown in Figs. 1 to 3, respectively.

Examples 6 to 9

[0152] Polymerization reactions were individually conducted in substantially the same manner as in Example 1, except that various amounts of 1-hexene were added to the polymerizer as a comonomer.

[0153] The reaction conditions, such as the amount of 1-hexene added, and results of the polymerization are shown in Tables 1 and 2.

[0154] With respect to each of the obtained polymers the relationship between the M_i and the Izod impact strength, the relationship between the M_i and the density (d), and the relationship between the M_i and the M_{iR} are shown in Figs. 1 to 3, respectively.

Comparative Examples 1 and 2

[0155] Polymerisation reactions were individually conducted in substantially the same manner as in Example 1 except

that (n-butylcyclopentadienyl)zirconium dichloride was employed instead of bis(indenyl)zirconium dichloride and that the amount of hydrogen introduced to the polymerizer was varied.

[0156] The reaction conditions and the results of the polymerisation are shown in Tables 1 and 2.

[0157] With respect to each of the obtained polymer, the relationship between the M_i and the Izod impact strength, the relationship between the M_i and the density (d) and the relationship between the M_i and the M_{IR} are shown in Figs. 1 to 3, respectively.

[0158] Further, with respect to ethylene polymers produced using a conventional Ziegler-Natta catalyst, the relationship between the M_i and the Izod impact strength and the relationship between the M_i and the density (d) are also shown in Figs. 1 and 2, respectively.

Table 1

	Zr (μ mol)	MAO (mmol)	H ₂ (ml) (NTP)	1-Hexene (mmol)	Yield (g)
Example 1	A, 1.0	0.3	192	0	43
Example 2	A, 1.0	0.3	128	0	47
Example 3	A, 1.0	0.3	91	0	45
Example 4	A, 1.0	0.3	64	0	47
Example 5	A, 1.0	0.3	290	0	46
Example 6	A, 1.0	0.3	189	40	40
Example 7	A, 1.0	0.3	131	40	48
Example 8	A, 1.0	0.3	67	40	43
Example 9	A, 1.0	0.3	185	80	45
Comparative Example 1	B, 1.0	0.3	40	0	45
Comparative Example 2	B, 1.0	0.3	80	0	48

[Note]

A: bis(indenyl)zirconium dichloride

B: bis(n-butylcyclopentadienyl)zirconium dichloride

MAO: methylaluminoxane

Table 2

	M _I (g/10 min)	HMI (g/10 min)	M _{IR}	Density, d (g/cm ³)	Amount of Comonomer (mol%)	M _w	M _w /M _n	Izod Impact Strength (kgf·cm/cm ²)
Example 1	25.1	862	34.3	0.9741	—	46,000	8.2	3.5
Example 2	19.8	747	37.7	0.9736	—	49,000	8.1	4.5
Example 3	11.1	372	33.5	0.9712	—	58,000	8.0	7.0
Example 4	5.7	175	31.0	0.9698	—	70,000	7.9	12.0
Example 5	30.1	1170	38.9	0.9765	—	43,000	8.7	3.5
Example 6	27.0	945	35.0	0.9703	0.07	45,000	8.3	4.0
Example 7	21.1	789	37.4	0.9691	0.09	48,000	8.2	5.0
Example 8	6.4	202	31.5	0.9655	0.05	68,000	8.0	13.5
Example 9	24.5	831	33.9	0.9651	0.15	47,000	8.1	4.5
Comparative Example 1	5.9	117	20.0	0.9642	—	66,000	2.7	9.5
Comparative Example 2	18.1	433	23.9	0.9684	—	47,000	2.8	2.5

INDUSTRIAL APPLICABILITY

[0159] The high density ethylene polymer of the present invention has excellent moldability, such as high melt flowability and excellent extrusion moldability, so that the ethylene polymer can be advantageously used especially in injection molding method. Further, the high density ethylene polymer of the present invention can be advantageously used for producing an excellent molded article which has not only excellent mechanical properties, such as high impact resistance and high stiffness, but also excellent appearance, such as high transparency and excellent surface gloss.

Claims

1. A high density ethylene polymer comprising a homopolymer of ethylene, or a copolymer of ethylene with at least one comonomer selected from the group consisting of an α -olefin, a cyclic olefin, and linear, branched and cyclic dienes, and having the following properties (a) to (h):

- (a) a density d (g/cm³) of from 0.951 to 0.980;
- (b) an M_I (g/10 minutes) of more than 5 and not more than 100, wherein M_I is defined as the melt flow rate as measured at 190 °C under a load of 2.16 kg;
- (c) said ethylene polymer satisfying the following relationship:

$$\log a_{KI} \geq -0.844 \log M_I + 1.462$$

wherein M_I is as defined above, and a_{KI} represents the Izod impact strength (kgf-cm/cm²);

- (d) said ethylene polymer satisfying the following relationship:

$$\log M_{IR} \geq -0.094 \log M_I + 1.520$$

wherein M_I is as defined above, and M_{IR} represents the H_{MI}/M_I ratio in which H_{MI} (g/10 minutes) is defined as the melt flow rate as measured at 190 °C under a load of 21.6 kg and M_I is as defined above; wherein

- (e) said density d (g/cm³) and said M_I (g/10 minutes) satisfy the following relationship:

$$d \geq -0.00873 \log M_I + 0.972, \text{ and}$$

- (f) said M_{IR} is not less than 25 and not more than 40;
- (g) an M_w of 30,000 or more, wherein M_w is defined as a weight average molecular weight measured by gel permeation chromatography; and
- (h) an M_w/M_n ratio in the range of from 5.0 to 10.0, wherein M_w and M_n , respectively, represent the weight average molecular weight and the number average molecular weight, each measured by gel permeation chromatography.

2. The high density ethylene polymer according to claim 1, which is an injection molding material.

3. The high density ethylene polymer according to claim 1 or 2, wherein said density d is 0.955 or more.

4. The high density ethylene polymer according to any one of claims 1 to 3, which is a copolymer of ethylene with at least one comonomer selected from the group consisting of a C₃-C₂₀ cyclic olefin, C₄-C₂₀ linear and cyclic dienes, C₅-C₂₀ branched dienes and an α -olefin represented by the formula $H_2C = CHR^{15}$ wherein R¹⁵ is methyl, ethyl, a C₃-C₁₈ linear, branched or cyclic alkyl group or a C₆-C₂₀ aryl group, said comonomer being present in an amount of not more than 1 mole %, based on the total number of moles of all monomer units constituting said ethylene polymer.

5. The ethylene polymer according to claim 4, wherein said comonomer is selected from the group consisting of propylene, 1-butene, 1-pentene, 1-hexene, 4-methyl-1-pentene, 1-octene, 1-decene, 1-dodecene, 1-tetradecene, 1-hexadecene, 1-octadecene, 1-eicosene, vinylcyclohexane, cyclopentene, cycloheptene, norbornene, 5-methyl-2-norbornene, tetracyclododecene, 2-methyl-1,4, 5,8-dimethano-1,2,3,4,4a,5,8,8a-octahydronaphthalene,

1,3-butadiene, 1,4-pentadiene, 1,5-hexadiene, 1,4-hexadiene, and cyclohexadiene.

6. A method for producing a high density ethylene polymer of claim 1, which comprises homopolymerizing ethylene or copolymerizing ethylene with at least one comonomer selected from the group consisting of an α -olefin, a cyclic olefin, and linear, branched and cyclic dienes, in the presence of a catalyst comprising the following components (A), (B) and (C):

(A) a transition metal compound represented by the formula (1)



wherein:

M represents a transition metal selected from the group consisting of zirconium, titanium and hafnium; each of R^1 and R^2 independently represents:

an indenyl group which is unsubstituted or substituted with at least one substituent selected from the group consisting of a C_1 - C_{20} alkyl group, a C_6 - C_{20} aryl group, an aralkyl group having a C_1 - C_{20} alkyl group substituted with at least one C_6 - C_{20} aryl group, and an alkylaryl group having a C_6 - C_{20} aryl group substituted with at least one C_1 - C_{20} alkyl group, wherein each alkyl group is independently of a linear, a branched or a cyclic configuration and wherein at least one carbon atom of said at least one substituent is optionally replaced by a silicon atom, said substituted indenyl group optionally having a substitution in which at least two positions thereof together are substituted with one substituent group, having a valence of two or more, derived from a substituent selected from said at least one substituent, said substituted indenyl group optionally having at least one substituent thereof bonded thereto through an oxygen, a nitrogen, a sulfur or a phosphorus atom;

each of R^3 and R^4 independently represents a hydrogen atom, a halogen atom, a C_1 - C_{20} alkyl group, a C_6 - C_{20} aryl group, an aralkyl group having a C_1 - C_{20} alkyl group substituted with at least one C_6 - C_{20} aryl group, an alkylaryl group having a C_6 - C_{20} aryl group substituted with a C_1 - C_{20} alkyl group, or a $-SO_3R^5$ group wherein R^5 is a C_1 - C_8 hydrocarbon group which is unsubstituted or substituted with at least one halogen atom, wherein each alkyl group is independently of a linear, a branched or a cyclic configuration and wherein at least one carbon atom of at least one of said alkyl, aryl, aralkyl and alkylaryl groups is optionally replaced by a silicon atom; and each of R^1 , R^2 , R^3 and R^4 is bonded to said transition metal M;

(B) an inorganic solid component comprising a particulate inorganic solid (b-1) having hydroxyl groups on a surface thereof and, carried thereon, an organoaluminumoxy compound (b-2) having repeating alkyloxyaluminum units each represented by the formula (5)



wherein R^6 represents a C_1 - C_{12} linear, branched or cyclic alkyl group; and (C) an organoaluminum compound,

wherein said components (B) and (C) are intimately mixed and contacted with each other to form an intimate mixture of components (B) and (C), and said intimate mixture and said component (A) are separately introduced into a system for homopolymerizing or copolymerizing ethylene, followed by polymerization.

7. The method according to claim 6, wherein said component (C) is a compound represented by the following formula

(6) or (7):



wherein R^7 represents a C_1 - C_{12} linear, branched or cyclic alkyl group or a C_6 - C_{20} aryl group; X represents a halogen atom or a hydrogen atom; and n is an integer of from 1 to 3; or



wherein R^7 is as defined for formula (6); Y represents an $-OR^8$ group, an $-OSiR_3^9$ group, an $-AlR_2^{10}$ group, an $-NR_2^{11}$ group, an $-SiR_3^{12}$ group or an $-N(R^{13})AlR_2^{14}$ group, wherein each of R^8 , R^9 , R^{10} and R^{14} independently represents a C_1 - C_{12} alkyl group or a C_6 - C_{20} aryl group, R^{11} represents a hydrogen group, a C_1 - C_{12} alkyl group, a C_6 - C_{20} aryl group or a silyl group which is unsubstituted or substituted with at least one C_1 - C_{12} alkyl group, and each of R^{12} and R^{13} independently represents a C_1 - C_{12} alkyl group, with the proviso that each alkyl group is independently of a linear, a branched or a cyclic configuration; and n is 1 or 2.

8. The method according to claim 6 or 7, wherein, in said component (B), said particulate inorganic solid (b-1) having hydroxyl groups on the surface thereof is at least one member selected from the group consisting of SiO_2 , Al_2O_3 , MgO , ZrO_2 , TiO_2 , B_2O_3 , CaO , ZnO , BaO , V_2O_5 , Cr_2O_3 and ThO_2 .
9. The method according to claim 6 or 7, wherein, in said component (B), said particulate inorganic solid (b-1) having hydroxyl groups on the surface thereof is silica.
10. The method according to any one of claims 6 to 9, wherein, in copolymerizing ethylene, ethylene is copolymerized with at least one comonomer selected from the group consisting of a C_3 - C_{20} cyclic olefin, C_4 - C_{20} linear and cyclic dienes, C_5 - C_{20} branched dienes and an α -olefin represented by the formula $H_2C = CHR^{15}$ wherein R^{15} is methyl, ethyl, a C_3 - C_{18} linear, branched or cyclic alkyl group or a C_6 - C_{20} aryl group.

Patentansprüche

1. Ethylenpolymer hoher Dichte, welches ein Homopolymer aus Ethylen oder ein Copolymer von Ethylen mit mindestens einem Comonomer enthält, das aus der Gruppe ausgewählt ist, die aus einem α -Olefin, einem cyclischen Olefin und linearen, verzweigten und cyclischen Dienen besteht, und das die folgenden Eigenschaften (a) bis (h) hat:

- (a) eine Dichte d (g/cm^3) von 0,951 bis 0,980;
- (b) eine M_I (g/10 Minuten) von mehr als 5 und nicht mehr als 100, worin M_I als der Schmelzindex definiert ist, der bei 190°C unter einer Belastung von 2,16 kg gemessen wird
- (c) das Ethylenpolymer erfüllt die folgende Beziehung:

$$\log a_{KI} \geq -0,844 \log M_I + 1,462$$

- worin M_I wie vorstehend definiert ist und a_{KI} die Kerbschlagzähigkeit nach Izod ($kgf \cdot cm/cm^2$) darstellt;

- (d) das Ethylenpolymer erfüllt die folgende Beziehung:

$$\log M_{IR} \geq -0,094 \cdot \log M_I + 1,520$$

- worin M_I wie vorstehend definiert ist und M_{IR} das Verhältnis H_{MI}/M_I darstellt, worin H_{MI} (g/10 Minuten) als Schmelzindex definiert ist, der bei 190°C unter einer Belastung von 21,6 kg und gemessen wird, und M_I wie vorstehend definiert ist;

worin


- (e) die Dichte d (g/cm^3) und M_I (g/10 Minuten) die folgende Beziehung erfüllen:

$$d \geq -0,00873 \log M_I + 0,972 \text{ und}$$

- (f) M_{IR} nicht weniger als 25 und nicht mehr als 40 ist;
 (g) ein M_w von 30 000 oder mehr, worin M_w als Gewichtsmittel des Molekulargewichts, gemessen durch Gelpermeationschromatographie, definiert ist; und
 (h) ein Verhältnis M_w/M_n im Bereich von 5,0 bis 10,0 worin M_w bzw. M_n das Gewichtsmittel des Molekulargewichts bzw. das Zahlenmittel des Molekulargewichts darstellen, jeweils gemessen durch Gelpermeationschromatographie.

2. Ethylenpolymer hoher Dichte nach Anspruch 1, welches ein Spritzgießmaterial ist.
3. Ethylenpolymer hoher Dichte nach Anspruch 1 oder 2, worin die Dichte d 0,955 oder höher ist.
4. Ethylenpolymer hoher Dichte nach einem der Ansprüche 1 bis 3, welches ein Copolymer von Ethylen mit mindestens einem Comonomer ist, das aus der Gruppe ausgewählt ist, die aus einem C_3 - C_{20} cyclischen Olefin, C_4 - C_{20} linearen und cyclischen Dienen, C_5 - C_{20} verzweigten Dienen und einem α -Olefin besteht, das durch die Formel $H_2C = CHR^{15}$ dargestellt ist, worin R^{15} Methyl, Ethyl, eine C_3 - C_{20} lineare, verzweigte oder cyclische Alkylgruppe oder eine C_6 - C_{20} -Arylgruppe ist, wobei das Comonomer in einer Menge von nicht mehr als 1 Mol-%, bezogen auf die Gesamtmolzahl aller Monomereinheiten, die in dem Ethylenpolymer enthalten sind, vorhanden ist.
5. Ethylenpolymer nach Anspruch 4, worin das Comonomer aus der Gruppe ausgewählt ist, die aus Propylen, 1-Buten, 1-Penten, 1-Hexen, 4-Methyl-1-penten, 1-Octen, 1-Decen, 1-Dodecen, 1-Tetradecen, 1-Hexadecen, 1-Octadecen, 1-Eicosen, Vinylcyclohexan, Cyclopenten, Cyclohepten, Norbornen, 5-Methyl-2-norbornen, Tetracyclododecen, 2-Methyl-1,4, 5,8-dimethan-1,2,3,4,4a,5,8,8a-octahydronaphthalin, 1,3-Butadien, 1,4-Pentadien, 1,5-Hexadien, 1,4-Hexadien und Cyclohexadien ausgewählt ist.
6. Verfahren zur Herstellung eines Ethylenpolymers hoher Dichte nach Anspruch 1, welches die Homopolymerisation von Ethylen oder die Copolymerisation von Ethylen mit mindestens einem Comonomer, das aus der Gruppe ausgewählt ist, die aus einem α -Olefin, einem cyclischen Olefin und linearen, verzweigten und cyclischen Dienen besteht, in Anwesenheit eines Katalysators umfaßt, der die folgenden Komponenten (A), (B) und (C) enthält:

(A) eine Übergangsmetallverbindung der Formel (1)



worin:

M ein Übergangsmetall darstellt, das aus der aus Zirkonium, Titan und Hafnium bestehenden Gruppe ausgewählt ist;

R^1 und R^2 jeweils unabhängig voneinander darstellen:

eine Indenylgruppe, die unsubstituiert oder mit mindestens einem Substituenten substituiert ist, der aus der aus einer C_1 - C_{20} -Alkylgruppe, einer C_6 - C_{20} -Arylgruppe, einer Aralkylgruppe mit einer C_1 - C_{20} -Alkylgruppe, die mit mindestens einer C_6 - C_{20} -Arylgruppe substituiert ist, und einer Alkylarylgruppe mit einer C_6 - C_{20} -Arylgruppe, die mit mindestens einer C_1 - C_{20} -Alkylgruppe substituiert ist, bestehenden Gruppe ausgewählt ist, worin jede Alkylgruppe unabhängig voneinander eine lineare, verzweigte oder cyclische Konfiguration einnimmt und worin mindestens ein Kohlenstoffatom des mindestens einen Substituenten gegebenenfalls durch ein Siliciumatom ersetzt ist, worin die substituierte Indenylgruppe gegebenenfalls eine Substitution aufweist, worin mindestens zwei Positionen gemeinsam mit einer Substituentengruppe substituiert sind, welche zweioder höherwertig ist und von einem Substituenten abgeleitet ist, der unter dem mindestens einen Substituenten ausgewählt ist, worin die substituierte Indenylgruppe gegebenenfalls mindestens einen Substituenten aufweist, der über ein Sauerstoff-, Stickstoff-, Schwefel- oder ein Phosphoratom daran gebunden ist;

R³ und R⁴ jeweils unabhängig voneinander ein Wasserstoffatom, ein Halogenatom, eine C₁-C₂₀-Alkylgruppe, eine C₆-C₂₀-Alkylgruppe, eine Aralkylgruppe mit einer C₁-C₂₀-Alkylgruppe, die mit mindestens einer C₆-C₂₀-Arylgruppe substituiert ist, eine Alkylarylgruppe mit einer C₆-C₂₀-Arylgruppe, die mit mindestens einer C₁-C₂₀-Alkylgruppe substituiert ist, oder eine -SO₃R⁵-Gruppe darstellen, worin R⁵ eine C₁-C₈-Kohlenwasserstoffgruppe ist, die unsubstituiert oder mit mindestens einem Halogenatom substituiert ist, worin jede Alkylgruppe unabhängig eine lineare, verzweigte oder cyclische Konfiguration aufweist und worin mindestens ein Kohlenstoffatom mindestens einer der Alkyl-, Aryl-, Aralkyl- und Alkylarylgruppen gegebenenfalls durch ein Siliciumatom ersetzt ist; und

R¹, R², R³ und R⁴ jeweils an das Übergangsmetall M gebunden sind;

(B) eine anorganische feste Komponente, die einen teilchenförmigen anorganischen Feststoff (b-1) mit Hydroxygruppen an dessen Oberfläche und, davon getragen, eine Organoaluminoxyverbindung (b-2) mit wiederkehrenden Alkyloxyaluminiumeinheiten der Formel (5) hat



worin R⁶ eine C₁-C₁₂-lineare, verzweigte oder cyclische Alkylgruppe darstellt; und

(C) eine Organoaluminiumverbindung,

worin die Komponenten (B) und (C) innig vermischt werden und unter Bildung eines innigen Gemisches der Komponenten (B) und (C) miteinander in Berührung stehen, und wobei das innige Gemisch und die Komponente (A) getrennt voneinander in ein System für die Homopolymerisation oder Copolymerisation von Ethylen eingeführt werden und danach die Polymerisation durchgeführt wird.

7. Verfahren nach Anspruch 6, wobei die Komponente (C) eine Verbindung ist, die durch die folgende Formel (6) oder (7) dargestellt ist:



worin R⁷ eine C₁-C₁₂-lineare, verzweigte oder cyclische Alkylgruppe oder eine C₆-C₂₀-Arylgruppe darstellt; X ein Halogenatom oder ein Wasserstoffatom darstellt und n eine ganze Zahl von 1 bis 3 ist; oder



worin R⁷ wie in Formel (6) definiert ist, Y eine -OR⁸-Gruppe, eine -OSiR⁹-Gruppe, eine -AlR¹⁰-Gruppe, eine -NR¹¹-Gruppe, eine -SiR¹²-Gruppe, oder eine -N(R¹³)AlR¹⁴-Gruppe ist, worin R⁸, R⁹, R¹⁰ und R¹⁴ jeweils unabhängig voneinander eine C₁-C₁₂-Alkylgruppe oder eine C₆-C₂₀-Arylgruppe darstellen, R¹¹ ein Wasserstoffatom, eine C₁-C₁₂-Alkylgruppe, eine C₆-C₂₀-Arylgruppe oder eine Silylgruppe darstellt, die unsubstituiert oder mit mindestens einer C₁-C₁₂-Alkylgruppe substituiert ist, eine und R¹² und R¹³ jeweils unabhängig voneinander eine C₁-C₁₂-Alkylgruppe darstellen, mit der Maßgabe, daß jede Alkylgruppe unabhängig voneinander eine lineare, verzweigte oder cyclische Konfiguration aufweist, und n 1 oder 2 ist.

8. Verfahren nach Anspruch 6 oder 7, wobei in der Komponente (B) der teilchenförmige anorganische Feststoff (b-1) mit Hydroxygruppen auf dessen Oberfläche mindestens ein Mitglied der Gruppe ist, die aus SiO₂, Al₂O₃, MgO, MgCl₂, ZrO₂, TiO₂, B₂O₃, CaO, ZnO, BaO, V₂O₅, Cr₂O₃ und ThO₂ besteht.
9. Verfahren nach Anspruch 6 oder 7, wobei in der Komponente (B) der teilchenförmige anorganische Feststoff (b-1) mit Hydroxygruppen auf dessen Oberfläche Siliciumdioxid ist.

10. Verfahren nach einem der Ansprüche 6 bis 9, wobei bei der Copolymerisation von Ethylen das Ethylen mit mindestens einem Comonomer copolymerisiert wird, das aus der Gruppe ausgewählt ist, die aus einem C₃-C₂₀ cyclischen Olefin, C₄-C₂₀ linearen und cyclischen Dienen, C₅-C₂₀ verzweigten Dienen und einem α-Olefin besteht, das durch die Formel H₂C = CHR¹⁵ dargestellt ist, worin R¹⁵ eine Methyl-, Ethyl-, eine C₃-C₁₈ lineare, verzweigte oder cyclische Alkylgruppe oder eine C₆-C₂₀-Arylgruppe ist.

Revendications

1. Polymère d'éthylène à haute densité comprenant un homopolymère d'éthylène, ou un copolymère d'éthylène avec au moins un comonomère choisi dans le groupe comprenant une α-oléfine, une oléfine cyclique et des diènes linéaires, ramifiés et cycliques, et ayant les propriétés (a) à (h) suivantes :

(a) une densité d (g/cm³) de 0,951 à 0,980;

(b) un M_l (g/10 minutes) de plus de 5 et de pas plus de 100, dans lequel M_l est défini par le débit de masse fondue tel que mesuré à 190°C sous une charge de 2,16 kg;

(c) ledit polymère d'éthylène satisfaisant à la relation suivante :

$$\log a_{kl} \geq -0,844 \log M_l + 1,462$$

dans laquelle M_l est tel que défini précédemment, et a_{kl} représente la résistance au choc Izod (kgf.cm/cm²);

(d) ledit polymère d'éthylène satisfaisant à la relation suivante :

$$\log M_{IR} \geq -0,094 \log M_l + 1,520$$

dans laquelle M_l est tel que défini précédemment, et M_{IR} représente le rapport H_{Ml}/M_l dans lequel H_{Ml} (g/10 minutes) est défini par le débit de masse fondue tel que mesuré à 190°C sous une charge de 21,6 kg et M_l est tel que défini précédemment; dans lequel

(d) la densité d (g/cm³) et le M_l (g/10 minutes) précités satisfont à la relation suivante :

$$d \geq -0,00873 \log M_l + 0,972, \text{ et}$$

(f) ledit M_{IR} n'est pas inférieur à 25 et pas supérieur à 40;

(g) un Mw de 30.000 ou plus, dans lequel Mw est défini par le poids moléculaire moyen pondéral mesuré par chromatographie de perméation sur gel; et

(h) un rapport Mw/Mn allant de 5,0 à 10,0, dans lequel Mw et Mn représentent, respectivement, le poids moléculaire moyen pondéral et le poids moléculaire moyen numérique, chacun mesuré par chromatographie de perméation sur gel.

2. Polymère d'éthylène à haute densité suivant la revendication 1, qui est une matière de moulage par injection.

3. Polymère d'éthylène à haute densité suivant l'une ou l'autre des revendications 1 et 2, dans lequel la densité précitée d est de 0,955 ou plus.

4. Polymère d'éthylène à haute densité suivant l'une quelconque des revendications 1 à 3, qui est un copolymère d'éthylène et d'au moins un comonomère choisi dans le groupe comprenant une oléfine cyclique en C₃-C₂₀, les diènes linéaires et cycliques en C₄-C₂₀, les diènes ramifiés en C₅-C₂₀ et une α-oléfine représentée par la formule H₂C = CHR¹⁵ dans laquelle R¹⁵ est du méthyle, de l'éthyle, un groupe alkyle linéaire, ramifié ou cyclique en C₃-C₁₈ ou un groupe aryle en C₆-C₂₀, ledit comonomère étant présent en une quantité de pas plus de 1 mole %, par rapport au nombre total de moles de toutes les unités de monomère constituant le polymère d'éthylène précité.

5. Polymère d'éthylène suivant la revendication 4, dans lequel le comonomère précité est choisi dans le groupe comprenant le propylène, le 1-butène, le 1-pentène, le 1-hexène, le 4-méthyl-1-pentène, le 1-octène, le 1-décène, le 1-dodécène, le 1-tétradécène, le 1-hexadécène, le 1-octadécène, le 1-éicosène, le vinylcyclohexane, le cyclopentène, le cycloheptène, le norbornène, le 5-méthyl-2-norbornène, le tétracyclododécène, le 2-méthyl-1.4, 5.8-di-

méthano-1,2,3,4,4a,5,8,8a-octahydronaphtalène, le 1,3-butadiène, le 1,4-pentadiène, le 1,5-hexadiène, le 1,4-hexadiène et le cyclohexadiène.

6. Procédé de production d'un polymère d'éthylène à haute densité suivant la revendication 1, qui comprend l'homopolymérisation d'éthylène ou la copolymérisation d'éthylène avec au moins un comonomère choisi dans le groupe comprenant une α -oléfine, une oléfine cyclique et des diènes linéaires, ramifiés et cycliques, en présence d'un catalyseur comprenant les composants (A), (B) et (C) suivants :

(A) un composé de métal de transition représenté par la formule (1) :



dans laquelle :

M représente un métal de transition choisi dans le groupe comprenant le zirconium, le titane et l'hafnium; R^1 et R^2 représentent chacun indépendamment un groupe indényle qui est non substitué ou substitué avec au moins un substituant choisi dans le groupe comprenant un groupe alkyle en C_1 - C_{20} , un groupe aryle en C_6 - C_{20} , un groupe aralkyle comportant un groupe alkyle en C_1 - C_{20} substitué avec au moins un groupe aryle en C_6 - C_{20} et un groupe alkylaryle comportant un groupe aryle en C_6 - C_{20} substitué avec au moins un groupe alkyle en C_1 - C_{20} , dans lesquels chaque groupe alkyle est indépendamment d'une configuration linéaire, ramifiée ou cyclique et dans lesquels au moins un atome de carbone d'au moins un substituant précité est éventuellement remplacé par un atome de silicium, ledit groupe indényle substitué comportant éventuellement une substitution dans laquelle au moins deux de ses positions ensemble sont substituées avec un groupe substituant, ayant une valence de 2 ou plus, provenant d'un substituant choisi parmi au moins le substituant précité, ledit groupe indényle substitué comportant éventuellement au moins un de ses substituants lié par un atome d'oxygène, d'azote, de soufre ou de phosphore;

R^3 et R^4 représentent chacun indépendamment un atome d'hydrogène, un atome d'halogène, un groupe alkyle en C_1 - C_{20} , un groupe aryle en C_6 - C_{20} , un groupe aralkyle comportant un groupe alkyle en C_1 - C_{20} substitué avec au moins un groupe aryle en C_6 - C_{20} , un groupe alkylaryle comportant un groupe aryle en C_6 - C_{20} substitué avec un groupe alkyle en C_1 - C_{20} , ou un groupe $-SO_3R^5$ dans lequel R^5 est un groupe hydrocarboné en C_1 - C_8 qui est non substitué ou substitué avec au moins un atome d'halogène, dans lesquels chaque groupe alkyle est indépendamment d'une configuration linéaire, ramifiée ou cyclique et dans lesquels au moins un atome de carbone d'au moins un des groupes alkyle, aryle, aralkyle et alkylaryle précités est éventuellement remplacé par un atome de silicium; et

R^1 , R^2 , R^3 et R^4 sont chacun liés au métal de transition M précité;

(B) un composant solide inorganique comprenant un solide inorganique particulière (b-1) comportant des groupes hydroxyle sur une de ses surfaces, et qui supporte un composé organoaluminomoxy (b-2) comportant des unités structurales d'alkyloxyaluminium représentées chacune par la formule (5) :



dans laquelle R^6 représente un groupe alkyle linéaire, ramifié ou cyclique en C_1 - C_{12} ; et
(C) un composé organoaluminique,

dans lequel les composants (B) et (C) précités sont intimement mélangés et mis en contact l'un avec l'autre pour former un mélange intime de composants (B) et (C), et ledit mélange intime et le composant (A) précités sont introduits séparément dans un système pour homopolymériser ou copolymériser de l'éthylène, opération suivie d'une polymérisation.

7. Procédé suivant la revendication 6, dans lequel le composant (C) précité est un composé représenté par la formule

(6) ou (7) suivante :



dans laquelle R^7 représente un groupe alkyle linéaire, ramifié ou cyclique en C_1-C_{12} ou un groupe aryle en C_6-C_{20} , X représente un atome d'halogène ou un atome d'hydrogène, et n est un nombre entier de 1 à 3; ou



dans laquelle R^7 est tel que défini pour la formule (6), Y représente un groupe $-\text{OR}^8$, un groupe $-\text{OSiR}_3^9$, un groupe $-\text{AlR}_2^{10}$, un groupe $-\text{NR}_2^{11}$, un groupe $-\text{SiR}_3^{12}$ ou un groupe $-\text{N(R}^{13})\text{AlR}_2^{14}$, dans lesquels R^8 , R^9 , R^{10} et R^{14} représentent chacun indépendamment un groupe alkyle en C_1-C_{12} ou un groupe aryle en C_6-C_{20} , R^{11} représente un atome d'hydrogène, un groupe alkyle en C_1-C_{12} , un groupe aryle en C_6-C_{20} ou un groupe silyle qui est non substitué ou substitué avec au moins un groupe alkyle en C_1-C_{20} , et R^{12} et R^{13} représentent chacun indépendamment un groupe alkyle en C_1-C_{12} , à la condition que chaque groupe alkyle soit indépendamment d'une configuration linéaire, ramifiée ou cyclique, et n est égal à 1 ou 2.

8. Procédé suivant l'une ou l'autre des revendications 6 et 7, dans lequel, dans le composant (B) précité, le solide inorganique particulaire (b-1) précité comportant des groupes hydroxyle à sa surface est au moins un membre choisi dans le groupe comprenant SiO_2 , Al_2O_3 , MgO , ZrO_2 , TiO_2 , B_2O_3 , CaO , ZnO , BaO , V_2O_5 , Cr_2O_3 et ThO_2 .
9. Procédé suivant l'une ou l'autre des revendications 6 et 7, dans lequel, dans le composant (B) précité, le solide inorganique particulaire (b-1) précité comportant des groupes hydroxyle à sa surface est de la silice.
10. Procédé suivant l'une quelconque des revendications 6 à 9, dans lequel, dans la copolymérisation d'éthylène, l'éthylène est copolymérisé avec au moins un comonomère choisi dans le groupe comprenant une oléfine cyclique en C_3-C_{20} , les diènes linéaires et cycliques en C_4-C_{20} , les diènes ramifiés en C_5-C_{20} et une α -oléfine représentée par la formule $\text{H}_2\text{C} = \text{CHR}^{15}$, dans laquelle R^{15} est du méthyle, de l'éthyle, un groupe alkyle linéaire, ramifié ou cyclique en C_3-C_{18} ou un groupe aryle en C_6-C_{20} .

FIG. 1




FIG. 2




FIG. 3




FIG.4

